
# X8R/X8L Dielectric








AVX has developed a range of multilayer ceramic capacitors designed for use in applications up to 150°C. These capacitors are manufactured with an X8R and an X8L dielectric material. X8R material has capacitance variation of  $\pm$ 15% between -55°C and +150°C. The X8L material has capacitance variation of  $\pm$ 15% between -55°C to 125°C and +15/-40% from +125°C to +150°C.

The need for X8R and X8L performance has been driven by customer requirements for parts that operate at elevated temperatures. They provide a highly reliable capacitor with low loss and stable capacitance over temperature.

They are ideal for automotive under the hood sensors, and various industrial applications. Typical industrial application would be drilling monitoring system. They can also be used as bulk capacitors for high temperature camera modules.

Both X8R and X8L dielectric capacitors are automotive AEC-Q200 qualified. Optional termination systems, tin, FLEXITERM® and conductive epoxy for hybrid applications are available. Providing this series with our FLEXITERM® termination system provides further advantage to customers by way of enhanced resistance to both, temperature cycling and mechanical damage.

#### PART NUMBER (see page 2 for complete part number explanation)



NOTE: Contact factory for availability of Termination and Tolerance Options for Specific Part Numbers.


			X	8 <b>R</b>												X8L							
SIZE		0	603		0805		1206		SIZE			0603			0805			1206					
	WVDC	25V	50V	25	V 5	60V 2	5V .	50V			WVE	C	25V	50V	100V	25V	50V	100V	16V	25V	50V	100V	
331	Cap 330	G	G	J		J			;	331	Cap	330		G	G		J	J					
471	(pF) 470	G	G	J		J				471	(pF)	470		G	G		J	J					
681	680	G	G	J		J				681		680		G	G		J	J					
102	1000	G	G	J		J	J	J		102		1000		G	G		J	J					
152	1500	G	G	J		J	J	J		152		1500		G	G		J	J			J	J	
222	2200	G	G	J		-	J	J		222		2200		G	G		J	J			J	J	
332	3300	G	G	J			J	J		332		3300		G	G		J	J			J	J	
472	4700	G	G	J		-	J	J		472		4700		G	G		J	J			J	J	
682	6800	G	G	J		-	J	J		682		6800		G	G		J	J			J	J	
103	Cap 0.01	G	G	J		-	J	J		103		0.01		G	G		J	J			J	J	
153	(µF) 0.015	G	G	J		-	J	J		153		).015	G	G		J	J	J			J	J	
223	0.022	G	G	J		-	J	J		223		).022	G	G		J	J	J			J	J	
333	0.033	G	G	J		J	J	J		333		0.033	G	G		J	J	N			J	J	
473	0.047	G	G	J		-	J	J		473		).047	G	G		J	J	N			J	J	
683	0.068	G		N			N	M		683	0	.068	G	G		J	J				J	J	
104	0.1			N			N	М		104		0.1	G	G		J	J				J	М	
154	0.15			N			N	М		154		0.15				J	N		J	J	J	Q	
224	0.22			N			N	M		224		0.22				N	N		J	J	J	Q	
334	0.33						N	М		334		0.33				N	_		J	M	P	Q	
474	0.47						N			474		0.47				N			M	M	Р		
684	0.68									684		0.68							M				
105	1	051/	5014					501/		105		1	051/	501/	1001	051/	501/	1001/	M	051/	501/	100V	
	WVDC	25V	50V	25	25V 50V			50V	_	WVDC		25V	50V	100V	25V	50V 100V		16V					
	SIZE	0603 0805					1206				SIZE			0603			0805			1206			
Lette	er A	C	E		G	J	J K		М		N			Q		X			Z			= AEC-Q200	
Max	. 0.33	0.5	6 0.	71	0.90	0.94	1.02	1	1.27		1.40 1.		52 1.78		2	29	2.54 2.		.79	Qualit		alified	
Thickn	<b>ess</b> (0.013			28)	(0.035)	(0.037)	(0.040	0) (0	.050)	50) (0.055		(0.0		(0.070)	(0.090)		(0.100		110)				
	PAPER EMBOSSED																						

# X8R/X8L Dielectric

## **General Specifications**

## **APPLICATIONS FOR X8R AND X8L CAPACITORS**

- All market sectors with a 150°C requirement
- Automotive on engine applications
- Oil exploration applications
- Hybrid automotive applications
  - Battery control
- Inverter / converter circuits
- Motor control applications
- Water pump
- Hybrid commercial applications
  - Emergency circuits
  - Sensors
  - Temperature regulation




#### ADVANTAGES OF X8R AND X8L MLC CAPACITORS

- Both ranges are qualified to the highest automotive AEC-Q200 standards
- Excellent reliability compared to other capacitor technologies
- RoHS compliant
- Low ESR / ESL compared to other technologies
- Tin solder finish
- FLEXITERM® available
- Epoxy termination for hybrid available
- 100V range available

### **ENGINEERING TOOLS FOR HIGH VOLTAGE MLC CAPACITORS**

- Samples
- Technical Articles
- Application Engineering
- Application Support



# X8R/X8L Dielectric





Parame	ter/Test	X8R/X8L Specification Limits	Measuring Conditions					
<b>Operating Temp</b>	perature Range	-55°C to +150°C	Temperature Cycle Chamber					
Capac	itance	Within specified tolerance	Freq.: 1.0 kHz ± 10%					
Dissipatio	on Factor	$\leq 2.5\%$ for $\geq 50V$ DC rating	Voltage: 1.0Vrms ± .2V					
Dissipatio		$\leq$ 3.5% for 25V DC and 16V DC rating						
Insulation I	Resistance	100,000MΩ or 1000MΩ - μF,	Charge device with rated voltage for					
Insulation	nesistance	whichever is less	$120 \pm 5$ secs @ room temp/humidity					
Distantia	Ohme with		Charge device with 300% of rated voltage for 1-5 seconds, w/charge and discharge current					
Dielectric	Strength	No breakdown or visual defects	limited to 50					
			Note: Charge device					
	Appearance	No defects	voltage for 500V devices. Deflection: 2mm					
	Capacitance		Test Time: 30 seconds					
Resistance to	Variation	≤ ±12%		7 1mm/sec				
Flexure	Dissipation							
Stresses	Factor	Meets Initial Values (As Above)						
	Insulation	≥ Initial Value x 0.3						
	Resistance							
Solder	rability	$\geq$ 95% of each terminal should be covered	Dip device in eutectic solder at $230 \pm 5^{\circ}$ C					
001001	-	with fresh solder	for 5.0 $\pm$ 0.5 seconds					
	Appearance Capacitance	No defects, <25% leaching of either end terminal						
	Variation	≤ ±7.5%						
	Dissipation		Dip device in eutectic solder at 260°C for 60 seconds. Store at room temperature for 24 ± 2 hours before measuring electrical properties.					
Resistance to	Factor	Meets Initial Values (As Above)						
Solder Heat	Insulation	· · · · · · · · · · · · · · · · · · ·						
	Resistance	Meets Initial Values (As Above)						
	Dielectric	Maata Initial ) (alwaa (Ala Albaya)						
	Strength	Meets Initial Values (As Above)						
	Appearance	No visual defects	Step 1: -55°C ± 2°	30 ± 3 minutes				
	Capacitance	$\leq \pm 7.5\%$	Step 2: Room Temp	≤ 3 minutes				
	Variation							
Thermal	Dissipation Factor	Meets Initial Values (As Above)	Step 3: +125°C ± 2°	$30 \pm 3$ minutes				
Shock	Insulation							
	Resistance	Meets Initial Values (As Above)	Step 4: Room Temp	≤ 3 minutes				
	Dielectric		Repeat for 5 cycles and measure after $24 \pm 2$ hours at room temperature					
	Strength	Meets Initial Values (As Above)						
	Appearance	No visual defects	Charge device with 1.5 rated voltage (≤ 10V) in test chamber set at 150°C ± 2°C					
	Capacitance	≤ ±12.5%						
	Variation							
	Dissipation	$\leq$ Initial Value x 2.0 (See Above)	for 1000 hours (+48, -0)					
Load Life	Factor		Remove from test chamber and stabilize at room temperature for 24 ± 2 hours before measuring.					
	Resistance	$\geq$ Initial Value x 0.3 (See Above)						
	Dielectric							
	Strength	Meets Initial Values (As Above)						
	Appearance	No visual defects	<ul> <li>Store in a test chamber set at 85°C ± 2°C/ 85% ± 5% relative humidity for 1000 hours (+48, -0) with rated voltage applied.</li> <li>Remove from chamber and stabilize at room temperature and humidity for 24 ± 2 hours before measuring.</li> </ul>					
	Capacitance	≤ ±12.5%						
	Variation							
Load	Dissipation	$\leq$ Initial Value x 2.0 (See Above)						
Humidity	Factor							
	Insulation	$\geq$ Initial Value x 0.3 (See Above)						
	Resistance Dielectric							
	Strength	Meets Initial Values (As Above)						
	Olichyll							

