



# Circuit Plating Tape

## 1285

### Technical Data

**Product Description** A polyester film tape with a rubber adhesive which resists plating and etching bath chemicals.

Product Construction	Backing	Adhesive	Color	Standard Roll Length
	Transparent Polyester	Rubber	Blue	144 yds. (132m)

**Typical Physical Properties** **Note:** The following technical information and data should be considered representative or typical only, and should not be used for specification purposes.

		ASTM Test Method
Adhesion to Steel:	30 oz./in. width (33 N/100mm)	D-3330
Tensile Strength (Break or Yield):	26 lbs./in. width (455 N/100mm)	D-3759
Elongation Break or Yield):	100%	D-3759
Backing Thickness:	1.0 mil (.03 mm)	
Total Tape Thickness:	3.7 mils (.09 mm)	D-3652

- General Information**
- Roller pressure must be monitored to insure clean, residue-free boards after tape removal. Air pressure controlled equipment can be set at 30 – 40 PSI. Non-air pressure controlled rollers should be set no closer than ½ the PC board thickness.
  - Heat should not be used during tape lamination.
  - The low stretch polyester film of 1285 tape is designed for machine and hand application.

**Shelf Life** To obtain best performance, use this product within 18 months from date of manufacture and store under normal conditions of 60° to 80°F (15° to 27°C) and 50% R.H. in the original carton

- Application Ideas**
- Masking of many printed circuit boards during solder stripping and precious metal plating of fingers.

Features	Features	Advantages	Benefits
	Polyester backing	Reduces stretch and recovery of tape and associated uneven stop-off line	Helps save money by reducing number of reject boards
	Thick adhesive coating	Reduces undercutting because adhesive helps block out solutions between fingers	Helps save time and money by reducing reject boards
	Specially designed adhesive	Eliminates silicone residue	Helps save money by eliminating silicone related board failures
		Reduces or eliminates the need for solvents	Reduces or eliminates solvent costs
		Higher adhesion requires less pressure to adhere to PC board surface	Saves on wear and replacement costs of rubber laminating rollers
		Eliminates white stain after leveling or fusing	Eliminates costly clean-up and rework
		Assures good anchorage of solder masks	Eliminates costly rework
		Assures good anchorage of conformal coatings	Eliminates costly rework
		Increases optimum solderability	Eliminates costly rework

### Technical Information and Data

The technical information and data, recommendations, and other statements provided in this document are based on tests or experience which 3M believes to be reliable, but the accuracy or completeness of such information is not guaranteed.

### Product Use

Please remember that many factors can affect the use and performance of a 3M product in a particular application. The materials to be used with the 3M product, the surface preparation of those materials, the product selected for use, the conditions in which the product is used, and the time and environmental conditions in which the product is expected to perform are among the many factors that can affect the use and performance of a 3M product. Given the variety of factors that can affect the use and performance of a 3M product, some of which are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

### Limited Warranty and Limited Remedy

The 3M product will be free from defects in material and manufacture for a period of one (1) year from the date of manufacture. 3M MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's method of application. If the 3M product is defective within the warranty period stated above, YOUR EXCLUSIVE REMEDY AND 3M'S SOLE OBLIGATION SHALL BE, AT 3M'S OPTION, TO REPLACE OR REPAIR THE 3M PRODUCT OR REFUND THE PURCHASE PRICE OF THE 3M PRODUCT.

### Limitation of Liability

Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including, but not limited to, contract, warranty, negligence, or strict liability.



This Industrial Tape and Specialties Division product was manufactured under a 3M quality system registered to ISO 9002 standards.



### Industrial Tape and Specialties Division

3M Center, Building 220-7W-03  
 St. Paul, MN 55144-1000  
 1 800 362 3550  
 1 800 223 7427 Fax on Demand  
[www.3M.com/industrialtape](http://www.3M.com/industrialtape)

© 3M IPC 2001  
 All rights reserved.

70-0703-0619-9  
 September/1/1999