## **Primary lithium battery** LS 14250

### 3.6 V Primary lithium-thionyl chloride (Li-SOCl<sub>2</sub>) High energy density <sup>1</sup>/<sub>2</sub>AA-size bobbin cell



1/2 R6 - 1/2 AA

### **Benefits**

- High voltage, stable during most of the application's lifetime
- Wide operating temperature range
- Low self-discharge rate (less than 1 % per year of storage at + 20°C)
- Easy integration into compact systems
- Superior resistance to atmospheric corrosion

### **Key features**

- Stainless steel container and end caps (low magnetic signature)
- Hermetic glass-to-metal sealing
- Non-flammable electrolyte
- Compliant with IEC 86-4 safety standard and IEC 60079-11 intrinsic safety standard
- Underwriters Laboratories (UL) Component Recognition (File Number MH 12609)
- Non-restricted for transport

### **Main applications**

- Utility metering
- Automatic meter reading
- Alarms and security devices
- Memory back-up
- Computer real-time clocks
- Tracking systems
- Automotive electronics
- Professional electronics

### **Cell size references**

Electrical characte	eristics	
(typical values relative	to cells stored for one year or less at +30°C max.]	
Nominal capacity		1.20 Ah
	) V cut-off. The capacity restored by the cell varies drain, temperature and cut-off)	
Open circuit voltage	(at + 20°C)	3.67 V
Nominal voltage	(at 0.1 mA + 20°C)	3.6 V
drained every 2 mn a current, yield voltage to the pulse characte	cally up to 100 mA (100 mA/0.1 second pulses, t + 20°C from undischarged cells with 10 μA base readings above 3.0 V. The readings may vary accord ristics, the temperature, and the cell's previous histor capacitor may be recommended in severe conditions.	0
Maximum recommended continuous current (Higher currents are possible, consult Saft)		35 mA
Storage	(recommended) (for more severe conditions, consult Saft)	+ 30°C (+ 86°F) max

Operating temperature range -60°C/+85°C (Operation above ambient T may lead to reduced capacity and (-76°F/+185°F) lower voltage readings at the beginning of pulses. Consult Saft)

### Physical characteristics

		14.65 mm (0.58 in)
		24.8 mm (0.98 in)
		8.9 g (0.3 oz)
		approx. 0.3 g
ffix CN, CNR 2 PF, 3 PF, 3 PF RP, 4 PF CNA (AX) El	radial tabs radial pins axial leads fiving leads	
ľ	CN, CNR 2 PF, 3 PF, 3 PF RP, 4 PF	CN, CNR radial tabs 2 PF, 3 PF, 3 PF RP, 4 PF radial pins CNA (AX) axial leads



### LS 14250

 $1.35 \pm 0.2$ 

0.4

Ø 14.5

± 0.15

Dimensions in mm.

 $24.5 \pm 0.3$ 


Ø 5.5

max


Ø 7.5 🔫

± 0.1

Voltage plateau versus Current and Temperature (at mid-discharge)








### Storage

• The storage area should be clean, cool (preferably not exceeding + 30°C), dry and ventilated.

### Warning

- Fire, explosion and burn hazard.
- Do not recharge, short circuit, crush, disassemble, heat above 100°C (212°F), incinerate, or expose contents to water.
- Do not solder directly to the cell (use tabbed cell versions instead).

#### Restored Capacity versus Current and Temperature (2.0 V cut-off)



#### Saft

Specialty Battery Group

12, rue Sadi Carnot 93170 Bagnolet - France Tel.: +33 (0)1 49 93 19 18 Fax: +33 (0)1 49 93 19 69

### www.saftbatteries.com

# Information in this document is subject to change without notice and becomes contractual only after written confirmation by Saft. For more details on primary lithium technologies please refer to Primary Lithium Batteries Selector Guide Doc N° 31048-2. Published by the Communications Department

Photo credit: Saft

Doc. Nº 31072-2-0308

Société anonyme au capital de 31 944 000 € RCS Bobigny B 383 703 873 Produced by Arthur Associates Limited.

