



REVISIONS

DOC. NO. SPC-F004 * Effective: 7/8/02 * DCP No: 1398

DCP #	REV	DESCRIPTION	DRAWN	DATE	CHECKD	DATE	APPRVD	DATE
1716	G	revised Lengths FPS-032 series	JWM	4/22/04	JC	4/22/04	JC	4/22/04
1857	H	RoHS Added	DCM	12/10/05	JWM	3/17/06	JWM	3/17/06

DESCRIPTION:



TYPE FPS (FPA) IS A SINGLE WALL FLEXIBLE HEAT SHRINK RADIATION CROSS-LINKED POLYOLEFIN TUBING. UPON THE APPLICATION OF HEAT IN EXCESS OF 250°F (121°C) TUBING SHRINKS AND CONFORMS TO THE GEOMETRY TO BE COVERED. CLEAR IS NOT UL RECOGNIZED OR CSA APPROVED. SHRINKAGE: 2:1

COLOR:

BLACK AND CLEAR IN ALL SIZES AND LENGTHS. GREEN, BLUE, RED, YELLOW AND WHITE AVAILABLE IN SOME PUT UP SIZES.

LENGTH:

4' (+1", -0"); 6" (±0.125") STANDARD

TYPE	SIZE (I.D.)	MINIMUM EXP. I.D.	MAXIMUM RECOVERED I.D.	RECOVERED NOM. WALL THICKNESS TOTAL WALL	PACKAGING (PER BOX)
FPS-003-1100-BLK	.046	.046	.023	.016	100' SPOOL
FPS-003-4025-BLK	.046	.046	.023	.016	(25) 4' LENGTHS
FPS-003-4025-CLR	.046	.046	.023	.016	(25) 4' LENGTHS
FPS-003-6040-BLK	.046	.046	.023	.016	(40) 6" LENGTHS
FPS-004-1100-BLK	.063	.063	.031	.017	100' SPOOL
FPS-004-4025-BLK	.063	.063	.031	.017	(25) 4' LENGTHS
FPS-004-4025-CLR	.063	.063	.031	.017	(25) 4' LENGTHS
FPS-004-4025-GRN	.063	.063	.031	.017	(25) 4' LENGTHS
FPS-004-6036-BLK	.063	.063	.031	.017	(36) 6" LENGTHS
FPS-004-6036-CLR	.063	.063	.031	.017	(36) 6" LENGTHS
FPS-004-6036-GRN	.063	.063	.031	.017	(36) 6" LENGTHS
FPS-006-1100-BLK	.093	.093	.046	.020	100' SPOOL
FPS-006-4025-BLK	.093	.093	.046	.020	(25) 4' LENGTHS
FPS-006-4025-CLR	.093	.093	.046	.020	(25) 4' LENGTHS
FPS-006-4025-GRN	.093	.093	.046	.020	(25) 4' LENGTHS
FPS-006-6032-BLK	.093	.093	.046	.020	(32) 6" LENGTHS
FPS-006-6032-GRN	.093	.093	.046	.020	(32) 6" LENGTHS
FPS-006-6032-WHT	.093	.093	.046	.020	(32) 6" LENGTHS
FPS-008-1100-BLK	.125	.125	.062	.020	100' SPOOL
FPS-008-4025-BLK	.125	.125	.062	.020	(25) 4' LENGTHS

SPC-F004.DWG

TOLERANCES: UNLESS OTHERWISE SPECIFIED, DIMENSIONS ARE FOR REFERENCE PURPOSES ONLY.	DRAWN BY:	DATE:	DRAWING TITLE:			
	JOSE PANGANIBAN	1/22/96	HEAT SHRINK TUBING			
	CHECKED BY:	DATE:	SIZE	DWG. NO.	ELECTRONIC FILE	REV
	JOHN COLE	7/13/96	A	TA-130	TA-130.DWG	H
APPROVED BY:	DATE:	SCALE: NTS		U.O.M.: INCHES		SHEET: 1 OF 4
JOHN LISZKA	7/14/98					

ALL RIGHTS RESERVED. NO PORTION OF THIS PUBLICATION, WHETHER IN WHOLE OR IN PART CAN BE REPRODUCED WITHOUT THE EXPRESS WRITTEN CONSENT OF SPC TECHNOLOGY. DISCLAIMER: ALL STATEMENTS AND TECHNICAL INFORMATION CONTAINED HEREIN ARE BASED UPON INFORMATION AND/OR TESTS WE BELIEVE TO BE ACCURATE AND RELIABLE. SINCE CONDITIONS OF USE ARE BEYOND OUR CONTROL, THE USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR THE INTENDED USE AND ASSUME ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH.

TYPE	SIZE (I.D.)	MINIMUM EXP. I.D.	MAXIMUM RECOVERED I.D.	RECOVERED NOM. WALL THICKNESS TOTAL WALL	PACKAGING (PER BOX)
FPS-008-4025-CLR	.125	.125	.062	.020	(25) 4' LENGTHS
FPS-008-4025-GRN	.125	.125	.062	.020	(25) 4' LENGTHS
FPS-008-6028-BLK	.125	.125	.062	.020	(28) 6" LENGTHS
FPS-008-6028-CLR	.125	.125	.062	.020	(28) 6" LENGTHS
FPS-008-6028-GRN	.125	.125	.062	.020	(28) 6" LENGTHS
FPS-008-6028-RED	.125	.125	.062	.020	(28) 6" LENGTHS
FPS-008-6028-WHT	.125	.125	.062	.020	(28) 6" LENGTHS
FPS-012-1100-BLK	.187	.187	.093	.020	100' SPOOL
FPS-012-4025-BLK	.187	.187	.093	.020	(25) 4' LENGTHS
FPS-012-4025-CLR	.187	.187	.093	.020	(25) 4' LENGTHS
FPS-012-4025-GRN	.187	.187	.093	.020	(25) 4' LENGTHS
FPS-012-6024-BLK	.187	.187	.093	.020	(24) 6" LENGTHS
FPS-012-6024-BLU	.187	.187	.093	.020	(24) 6" LENGTHS
FPS-012-6024-CLR	.187	.187	.093	.020	(24) 6" LENGTHS
FPS-012-6024-GRN	.187	.187	.093	.020	(24) 6" LENGTHS
FPS-012-6024-RED	.187	.187	.093	.020	(24) 6" LENGTHS
FPS-012-6024-WHT	.187	.187	.093	.020	(24) 6" LENGTHS
FPS-016-1100-BLK	.250	.250	.125	.025	100' SPOOL
FPS-016-4025-BLK	.250	.250	.125	.025	(25) 4' LENGTHS
FPS-016-4025-CLR	.250	.250	.125	.025	(25) 4' LENGTHS
FPS-016-4025-GRN	.250	.250	.125	.025	(25) 4' LENGTHS
FPS-016-6020-BLK	.250	.250	.125	.025	(20) 6" LENGTHS
FPS-016-6020-BLU	.250	.250	.125	.025	(20) 6" LENGTHS
FPS-016-6020-CLR	.250	.250	.125	.025	(20) 6" LENGTHS
FPS-016-6020-GRN	.250	.250	.125	.025	(20) 6" LENGTHS
FPS-016-6020-RED	.250	.250	.125	.025	(20) 6" LENGTHS
FPS-016-6020-WHT	.250	.250	.125	.025	(20) 6" LENGTHS
FPS-024-1100-BLK	.375	.375	.187	.025	100' SPOOL
FPS-024-4025-BLK	.375	.375	.187	.025	(25) 4' LENGTHS
FPS-024-4025-CLR	.375	.375	.187	.025	(25) 4' LENGTHS
FPS-024-4025-GRN	.375	.375	.187	.025	(25) 4' LENGTHS
FPS-024-6016-BLK	.375	.375	.187	.025	(16) 4' LENGTHS
FPS-024-6016-BLU	.375	.375	.187	.025	(16) 4' LENGTHS
FPS-024-6016-CLR	.375	.375	.187	.025	(16) 4' LENGTHS
FPS-024-6016-GRN	.375	.375	.187	.025	(16) 4' LENGTHS
FPS-024-6016-RED	.375	.375	.187	.025	(16) 4' LENGTHS
FPS-024-6016-WHT	.375	.375	.187	.025	(16) 4' LENGTHS

ALL RIGHTS RESERVED. NO PORTION OF THIS PUBLICATION, WHETHER IN WHOLE OR IN PART CAN BE REPRODUCED WITHOUT THE EXPRESS WRITTEN CONSENT OF SPC TECHNOLOGY.

SPC-F004.DWG

SIZE DWG. NO.

A

TA-130

ELECTRONIC FILE

TA-130.dwg

REV

G

DOC. NO. SPC-F004 * Effective: 7/8/02 * DCP No: 1398

SCALE: NTS

U.O.M.: INCHES [mm]

SHEET: 2 OF 4

TYPE	SIZE (I.D.)	MINIMUM EXP. I.D.	MAXIMUM RECOVERED I.D.	RECOVERED NOM. WALL THICKNESS	PACKAGING (PER BOX)
FPS-032-1100-BLK	.500	.500	.250	.025	100' SPOOL
FPS-032-4005-BLK	.500	.500	.250	.025	(5) 4' LENGTHS
FPS-032-4005-CLR	.500	.500	.250	.025	(5) 4' LENGTHS
FPS-032-4005-GRN	.500	.500	.250	.025	(5) 4' LENGTHS
FPS-032-6014-BLK	.500	.500	.250	.025	(14) 6" LENGTHS
FPS-032-6014-CLR	.500	.500	.250	.025	(14) 6" LENGTHS
FPS-032-6014-GRN	.500	.500	.250	.025	(14) 6" LENGTHS
FPS-032-6014-RED	.500	.500	.250	.025	(14) 6" LENGTHS
FPS-032-6014-WHT	.500	.500	.250	.025	(14) 6" LENGTHS
FPS-048-1050-BLK	.750	.750	.375	.030	50' SPOOL
FPS-048-4005-BLK	.750	.750	.375	.030	(5) 4' LENGTHS
FPS-048-4005-CLR	.750	.750	.375	.030	(5) 4' LENGTHS
FPS-048-4005-GRN	.750	.750	.375	.030	(5) 4' LENGTHS
FPS-048-6012-BLK	.750	.750	.375	.030	(12) 6" LENGTHS
FPS-048-6012-CLR	.750	.750	.375	.030	(12) 6" LENGTHS
FPS-048-6012-GRN	.750	.750	.375	.030	(12) 6" LENGTHS
FPS-064-1050-BLK	1.00	1.00	.500	.035	50' SPOOL
FPS-064-4005-BLK	1.00	1.00	.500	.035	(5) 4' LENGTHS
FPS-064-4005-CLR	1.00	1.00	.500	.035	(5) 4' LENGTHS
FPS-064-4005-GRN	1.00	1.00	.500	.035	(5) 4' LENGTHS
FPS-064-6008-BLK	1.00	1.00	.500	.035	(8) 6" LENGTHS
FPS-064-6008-GRN	1.00	1.00	.500	.035	(8) 6" LENGTHS
FPS-096-1050-BLK	1.50	1.50	.750	.040	50' SPOOL
FPS-096-4005-BLK	1.50	1.50	.750	.040	(5) 4' LENGTHS
FPS-096-4005-CLR	1.50	1.50	.750	.040	(5) 4' LENGTHS
FPS-096-6005-BLK	1.50	1.50	.750	.040	(5) 6" LENGTHS
FPS-096-6005-CLR	1.50	1.50	.750	.040	(5) 6" LENGTHS
FPS-128-1050-BLK	2.00	2.00	1.00	.045	50' SPOOL
FPS-128-4005-BLK	2.00	2.00	1.00	.045	(5) 4' LENGTHS
FPS-128-4005-CLR	2.00	2.00	1.00	.045	(5) 4' LENGTHS
FPS-128-6003-BLK	2.00	2.00	1.00	.045	(3) 6" LENGTHS
FPS-128-6003-BLU	2.00	2.00	1.00	.045	(3) 6" LENGTHS

ALL RIGHTS RESERVED. NO PORTION OF THIS PUBLICATION, WHETHER IN WHOLE OR IN PART CAN BE REPRODUCED WITHOUT THE EXPRESS WRITTEN CONSENT OF SPC TECHNOLOGY.

SPC-F004.DWG

SIZE DWG. NO.

A TA-130

ELECTRONIC FILE

TA-130.dwg

REV

G

DOC. NO. SPC-F004 * Effective: 7/8/02 * DCP No: 1398

SCALE: NTS

U.O.M.: INCHES [mm]

SHEET: 3 OF 4

TYPICAL PROPERTIES:

Physical

TENSILE STRENGTH	2400 PSI
ULTIMATE ELONGATION	400%
LONGITUDINAL CHANGE	±5%
SECANT MODULUS (2%)	1.7 X 10 ⁴ PSI
SPECIFIC GRAVITY	1.3 G/CM ² MAX (BLACK) .93 G/CM ² MAX (CLEAR)
HEAT AGING (336 HRS @ 175°C)	ELONGATION 175%
HEAT SHOCK (4 HRS @ 250°C)	NO DRIPPING, CRACKING,
LOW TEMPERATURE FLEXIBILITY: (4 HRS @ -55°C)	NO CRACKING
FLAMMABILITY	COLORED TUBING: SELF-EXTINGUISH; MEETS UL 224 ALL TUBING FLAME TEST (CLASS 1 ONLY) CLEAR TUBING: CLASS 2 (NON-FLAME RETARDANT)

UL RECOGNIZED:

E52331

CSA APPROVED:

LR382278M

MIL. SPEC. #:

I-23053/5 CLASS 1,2
AMS-3636, AMS-3637

Electrical

DIELECTRIC STRENGTH:	900 V/MIL
VOLUME RESISTIVITY	10 ¹⁵ OHM-CM

Chemical

CORROSIVE EFFECT	NON-CORROSIVE
SOLVENT RESISTANCE	
TENSILE STRENGTH	1000 PSI
DIELECTRIC STRENGTH	400 V/MIL
WATER ABSORPTION	0.2%
FUNGUS RESISTANCE	NON-NUTRIENT