



REVISIONS				DOC. NO. SPC-F004 * Effective: 7/8/02 * DCP No: 1398				
DCP #	REV	DESCRIPTION	DRAWN	DATE	CHECKD	DATE	APPRVD	DATE
294	C	Updated "Modified" added; Mil Spec added	J.W.M.	10/3/97	J.C.			
1199	D	Renamed - was KYS-0**-****-CLR	JWM	8/30/01	JC	11/6/01	JC	11/6/01

DESCRIPTION:

TYPE KYS IS AN IRRADIATED, THIN-WALL, HEAT SHRINKABLE TUBING FABRICATED FROM MODIFIED POLYVINYLIDENE FLUORIDE. UPON THE APPLICATION OF HEAT IN EXCESS OF 175°C, THE TUBING SHRINKS TO THE GEOMETRY OF THE PART TO BE COVERED.

SHRINKAGE: 2:1 COLOR: CLEAR

Dimensions				Standard Packages					
Size	Expanded I.D. (Min.)	Recovered I.D. (Max.)	Recovered Nominal Wall Thickness	4 Foot Lengths (+1", -0")			6 Inch Lengths (±.125")		
				SPC Type No.	Qty	Total Footage	SPC Type No.	Qty	Total Footage
3/64"	.046"	.023"	.010"	KYS-003-4025-CLR	25	100 FT	N/A	---	---
1/16"	.063"	.031"	.010"	KYS-004-4025-CLR	25	100 FT	KYS-004-6028-CLR	28	14 FT
3/32"	.093"	.046"	.010"	KYS-006-4025-CLR	25	100 FT	KYS-006-6024-CLR	24	12 FT
1/8"	.125"	.062"	.010"	KYS-008-4025-CLR	25	100 FT	KYS-008-6020-CLR	20	10 FT
3/16"	.187"	.093"	.010"	KYS-012-4025-CLR	25	100 FT	KYS-012-6016-CLR	16	8 FT
1/4"	.250"	.125"	.012"	KYS-016-4025-CLR	25	100 FT	KYS-016-6012-CLR	12	6 FT
3/8"	.375"	.187"	.012"	KYS-024-4025-CLR	25	100 FT	KYS-024-6008-CLR	8	4 FT
1/2"	.500"	.250"	.012"	KYS-032-4005-CLR	5	20 FT	KYS-032-6004-CLR	4	2 FT
3/4"	.750"	.375"	.017"	KYS-048-4005-CLR	5	20 FT	KYS-048-6002-CLR	2	1 FT

Typical Properties

Physical

Tensile Strength: 5500 PSI
 Ultimate Elongation: 350%
 Longitudinal Change: +1, -10%
 Specific Gravity: 1.7 g/cm² Max.
 Operating Temp: -55°C ~ +175°C
 Shrink Temp: 175°C (347°F)
 Low Temp. Flexibility (4 hrs @ -55°C): No Cracking
 Flammability: Self-Extinguishing-Meets UL 224, VW-1
 Flexibility*: 10

Electrical

Dielectric Strength: 900 V/Mil
 Volume Resistivity: 10¹⁴ Ohms-cm

Chemical

Corrosion Resistance: Non-Corrosive
 Fuel & Oil Resistance: Excellent
 Solvent Resistance: Excellent
 Abrasion Resistance: Excellent
 Acids & Alkalis Resistance: Excellent

MIL. Spec. Nos.

MIL-I-23053/8, AMS-3632
 MIL-I-2305318, Class 1



E52331

*Flexibility: The materials are rated on a scale of 1~10.
 1=most flexible and 10=most rigid

The technical information provided consists of typical product data and should not be used for specification purposes. Unless otherwise noted, all tests are performed at room temperature.

KYNAR® is a registered trade name of the Penwalt Chemical Co.

SPC-F004.DWG



TOLERANCES: UNLESS OTHERWISE SPECIFIED, DIMENSIONS ARE FOR REFERENCE PURPOSES ONLY.	DRAWN BY:	DATE:	DRAWING TITLE:			
	J.A.P.	2/20/92	General Purpose Kynar Heat Shrink Tubing			
	CHECKED BY:	DATE:	SIZE	DWG. NO.	ELECTRONIC FILE	REV
	JOHN COLE	2/20/92	A	TA-401	TA-401.dwg	D
APPROVED BY:	DATE:	SCALE: NTS		U.O.M.: INCHES [mm]		SHEET: 1 OF 1
John Cole	2/20/92					

ALL RIGHTS RESERVED. NO PORTION OF THIS PUBLICATION, WHETHER IN WHOLE OR IN PART CAN BE REPRODUCED WITHOUT THE EXPRESS WRITTEN CONSENT OF SPC TECHNOLOGY. DISCLAIMER: ALL STATEMENTS AND TECHNICAL INFORMATION CONTAINED HEREIN ARE BASED UPON INFORMATION AND/OR TESTS WE BELIEVE TO BE ACCURATE AND RELIABLE. SINCE CONDITIONS OF USE ARE BEYOND OUR CONTROL, THE USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR THE INTENDED USE AND ASSUME ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH.