3MTM Dri-Shield Moisture Barrier Bag 2700

Moisture Barrier Bag ~ Aluminized

3M's Dri-Shield 2700 Moisture Barrier Bag is designed for dry packaging of electronic devices. Made from multiple layers of metallized polyester and heavy gauge dissipative polyethylene, Dri-Shield 2700 bags provide superior puncture resistance and drop test performance. Bags protect SMD's from moisture and static damage. Flexible structure is easy to vacuum seal. Coded for QC traceability.

Standards

Meets electrical and physical requirements of MIL-PRF-81705 Type 1, EIA 583, EIA 541, EIA 625, and EOS/ESD Standards.

Specifications

Physical Properties: Typical Values

MVTR(g/100 sq.in./24 hrs) <.005 ASTM F 1249 Puncture Resistance 30 lbs FTMS 101 MTH 2065 Thickness 7.0 mils 3M 008 ASTM D882 Tensile Strength 40 lb Seam Strength Pass MIL-PRF-81705

Heat Sealing Conditions:

300°F - 400°F Temperature 0.6 - 4.5 seconds Time 30 - 70 PSI Pressure

Electrical Properties:

ASTM D257 <10¹² ohms/square <10¹² ohms/square ANSI/ESD STM11.11 <10¹¹ ohms Surface Resistivity / Resistance or <10¹¹ ohms Exterior or Metal 100 ohms

Static Shielding < 20 volts FIA 541 EOS/ESD S11.31 Static Shielding < 10 nJ **EMI** Attenuation 45 dB MIL-PRF-81705 Static Decay < 0.03 seconds FTMS 101 MTH 4046 FTMS 101 MTH 3005 Non-Corrosive Pass

Outgassing Pass ASTM E595

Dri-Shield 2700

Sizes on Page 2

3M™ Moisture Barrier Bag with 3M™ Humidity Indicator Card and





Material Structure

7.0 mils of static dissipative polyethylene and metallized polyester create an exceptional dry package with superior puncture performance. This premium material meets or exceeds

HEAVY GAUGE

the MVTR and EMI/RFI/Static STATIC DISSIPATIVE POLYESTER

Shielding requirements of MIL-PRF-81705 ALUMINUM SHIELD Type I and EIA

POLYESTER 583 Type I for ALUMINUM SHIELD static safe.

moisture barrier HEAVY GAUGE packaging. STATIC DISSIPATIVE POLYETHYLENE

See 3M Data Sheets for these related items:

Humidity Indicator Cards (HIC's)

Desiccant Vacuum Sealers

D U C D Α Н Α

Dri-Shield 2700 Moisture Barrier Bag ALUMINIZED

MOISTURE BARRIER BAG, ALUMINIZED

ITEM NUMBER D27(W")(L")

DATASHEET 1103-A

3M Electronic Solutions Division 6801 River Place Blvd. Austin TX 78726-9000 US and Canada: 866-722-3736 Fax: 866-722-3735

Intl: 919-718-0000; Fax: 919-774-8174

email: 3Mstaticinfo@mmm.com; www.3M.com/static

3M is a trademark of 3M Company. All other trademarks herein are the property of their respective owners.

3MTM Dri-Shield Moisture Barrier Bag 2700

Moisture Barrier Bag ~ Aluminized

W"x L" P/N	W"x L" P/N	W"x L" P/N
4 x 6 D2746	10 x 30 D271030	15 x 18 D271518
10 x 12 D271012	10.5 x 18 D2710.518	16 x 18 D271618
10 v 20 D271020	12 v 16 D271216	

- All standard sizes in-stock/same day shipment.
- Width is measured from inside seam to inside seam.
- Length is measured from the top edge to the bottom fold.
- Opening is in the "width" dimension.
- · Custom bag sizes, custom printing, and custom hot stamping are available.
- Most sizes are packed 100 per case. Small sizes are packed 1000 or 500 per case.

SEAL LENGTH

WIDTH

3MTM Dri-Shield 2700 Moisture Barrier Bag

FOLD

- SEAM

-OPENING

How Moisture Barrier Bags Work

Moisture barrier bags work by enclosing a device with a metal or plastic shield(s) that has a high resistance to moisture vapor permeation. Dry devices are placed inside this shield, and the moisture-laden air is evacuated. Desiccant filled pouches scavenge the remaining moisture from the bag's interior. Moisture that penetrates the bag is also entrapped by the desiccant. Humidity indicating cards report the effectiveness of the package upon device use. A label on the bag indicates the amount of exposure time devices are allowed prior to use, and the drying (re-baking) time and temperature if the exposure time is exceeded.

As the barrier property improves, the Moisture Vapor Transmission Rate (MVTR) decreases. Bags with lower MVTR provide better barrier. Aluminum foil provides the best MVTR of about 0.0003. Multiple layers of Aluminized Polyester can provide 0.02 to about 0.005.

Puncture Resistance is an important feature for barrier bags. Sharp tray edges may tear through bags with low puncture resistance.

Dri-Shield 2700 Moisture Barrier Bag ALUMINIZED

R O

D

MOISTURE BARRIER BAG, ALUMINIZED

ITEM NUMBER D27(W")(L")

U C T

DATASHEET

D A T

1103-A

3M Electronic Solutions Division 6801 River Place Blvd. Austin, TX 78726-9000 US and Canada: 866-722-3736 Fax: 866-722-3735

Intl: 919-718-0000; Fax: 919-774-8174

email: 3Mstaticinfo@mmm.com; www.3M.com/static

Н

3M is a trademark of 3M Company. All other trademarks herein are the property

of their respective owners

© 2008

