




Metallised Shielding Bags Buried Metal

Material Structure

- 1/ Static Dissipative Layer
- 2/ Polyester
- 3/ Aluminium Shielding Layer
- 4/ Static Dissipative Polyethylene



Conductive buried aluminium shielding layer between two polymeric plastic layers: exposed surface static dissipative.

Contains no amines, amides or n-octanoic acid.

- Can be Heat Sealed
- Available in various sizes
- Available with gripseal closure system

PHYSICAL PROPERTIES:

Yield (per pound)	8,750sq.in
Total Thickness	3.1 mils (80 micron)
Tensile Strength: (ASTM D 882-91, Method A)	MD: 5800 psi TD: 6600 psi
Tear Strength (D 1004-66 Notched)	MD: 2.5lbs TD: 85%
Elongation (ASTM D 882-91, Method A)	MD: 80% TD: 85%
Burst Strength (FTMS 101 C, Method 2007 la)	50 psi
Puncture Strength (FTMS 101C, Method 2065.1)	>12lbs
Heat Seal Strength (D1876-93) Vertod bar sealer/heat & dwell 5.5	>14lbs/in width (room temperature)
MVTR (ASTM F-1249 @ 100°F/100 sq in/24hrs)	0.3gms – nominal
Light Transmission (ASTM D-1003-92)	40% +/- 5%

ELECTRICAL PROPERTIES:

EMI Shielding (mili-B-81705C)	>10dB Between 1 & 10 GHZ
Resistivity – Conductive Metal Layer (ASTM D-257)	<50 ohms/sq. (5 x 10 ¹ ohm/sq)
Capacitive Probe Test (high Voltage Discharge) – (EIA – Std 541/Appendix E – 1KV)	<20 volts
Static Decay (FTMS 101C, Method 4046.1, 5000 to 0 volts)	< 0.03 Seconds
Surge Resistivity (both surfaces) – (ES011.11 @ 12% R.H.)	<10 ¹² ohms/sq (10 ¹⁰ ohm/sq typical)
Charge Generation – nominal (Modified incline plane average nC/sq.in)	Teflon: - 0.09 Quartz: +0.10

Antistat – The ESD Control Centre Limited, Unit 108 Claydon Industrial Pk, Gt Blakenham, Ipswich, Suffolk, UK. Tel: +44 (0) 1473 836 200 Fax: +44 (0) 1473 836 220
WWW.ANTISTAT.CO.UK

