

ESD Conductive Matting

Features:

- Available in cut form or roll
- Excellent heat / chemical resistance
- Available in a selection of colours



Economy Matting Specification:

Item:		Unit:	Value:	Test Method:
Tensile strength	Width	kg/X	105	KS 6518-91
	Length	-	114	-
Elongation	Width	%	380	-
	Length	-	370	-
Hardness	Length	HS	64	-
Tear Strength (B)	Width	kg/X	31	-
	Length	-	37	-
Temp. Resistance	-		Max 130	-
Surface Resistivity (RTT)	Black (under)	Ω /sqm	10E3 - 10E5	ASTM D257
	Black (upper)		10E7 - 10E9	-
Volume Resistivity	Black (under)	Ω /sqm	10E3 - 10E9	ASTM D257
	Black (upper)		10E7 - 10E9	
Static Decay (5,000 - 500V)	-	Second	<0.01	FTS 101C

Product Code:	Description:	Size:	Additional Notes:
1687911	ESD Conductive Matting - Smooth (with stud in each corner)	1.1m x 2.4m 1.3mm thickness	Black (Ref: 082-0002f5)

Disclaimer: This data sheet and its contents (the "Information") belong to the Premier Farnell Group (the "Group") or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but the Group assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where the Group was aware of the possibility of such loss or damage arising) is excluded. This will not operate to limit or restrict the Group's liability for death or personal injury resulting from its negligence. SPC Multicomp is the registered trademark of the Group. © Premier Farnell plc 2008.