PRODUCT DATASHEET		EVEREADY.				
		1-800-383-7323 USA/CAN www.energizer.com				
EVEREADY 504	Chemical System:	Zinc-Manganese Dioxide (Zn/Mn02)				
EURAPEIN NO. 804 NEDA 230 NEDA 230 FUCATIONS	Designation: Battery Voltage:	ANSI / NEDA-220, IEC-10F15 15 Volts				
Industry Standard Dimensions mm (inches) 6.40 (0.252) Dia.	Average Weight: Volume: Average Capacity:	15.1 grams (0.5 oz.) 8 cubic centimeters (0.5 cubic inch)				
<u>15.10 (0.594)</u> 13.90 (0.547)	Cells: Jacket:	Ten No. 110 in series Metal				
0.40 (0.016) Minimum (+)		PICAL DISCHARGE CURVE nulated Test @ 21°C (70°F)				
34.9 <u>0 (1</u> .374) 33.30 (1.311)	14 Closed Circuit Voltage 12 11 11 11 11 11 11 10 9 9	Schedule: 4 hours/day Typical Drain @ 12V: 0.4 mA Load: 30,000 ohms				
0.40 (0.016)	0 40	80 120 160 200 240 Service, Hours				

Simulated Application Test Estimated Average Service at 21°C (70°F)

		Cutoff Voltage							
at 12V Schedule: (milliamperes)	Load (ohms)	8V	97V	10V	11V	12V	13V		
			Hours						
4 hours/day	0.4	30,000	235	222	205	180	132	60	

Important Notice

This data sheet contains information specific to batteries manufactured at the time of its publication. **Contents herein do not constitute a warranty.** Copyright © Eveready Battery Co. Inc. - All Rights Reserved