PRODUCT DATASHEET	EVEREADY. 1-800-383-7323 USA/CAN www.energizer.com
EVEREADY 763	Chemical System: Zinc-Manganese Dioxide (Zn/Mn0 ₂)
$\frac{51.60}{50.00} (1.969) + - + + + + + + + + + + + + + + $	Designation:ANSI / NEDA-710Battery Voltage:22.5 VoltsAverage Weight:372 grams (13.2 oz.)Volume:311 cubic centimeters (19.0 cubic inch)Average Capacity:1,700 mAh to 0.8 volts/cell (Rated at 25 mA continuous drain at 21°C)Cells:Forty Five No. 130 Three parallel strings of fifteen in seriesJacket:Paper
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	TYPICAL DISCHARGE CURVE Simulated Test @ 21°C (70°F) 25.5 Schedule: 24 hours/day 22.5 Typical Drain @ 18V: 3.6 mA 19.5 Load: 5,000 ohms 116.5 10.5 0 75 150 225 0 75 150 225 300 375 450 525 Service, Hours 255 250 375 450 525

Simulated Application Test Estimated Average Service at 21°C (70°F)

	Typical Drains		Cutoff Voltage	
Schedule:	at 18V (milliamperes)	Load (ohms)	12V 13.5V 15V 16.5V 18V 19.5V	
			Hours	
24 hours/day	3.6	5,000	491 435 347 227	
4 hours/day	14.4	1,250	135 125 112 92 75 46	

Important Notice

This data sheet contains information specific to batteries manufactured at the time of its publication. Contents herein do not constitute a warranty. Copyright © Eveready Battery Co. Inc. - All Rights Reserved