

# ENGINEERING DATASHEET

**EVEREADY BATTERY CO.** Internet: www.energizer.com


1-800-383-7323 / USA 1-800-383-7323 / CANADA

+ 44 (0) 208 920 2306 / EUROPE


# **ENERGIZER NO. NH12**




# Industry Standard Dimensions in mm (inches)



# TYPICAL DISCHARGE CHARACTERISTICS Average Performance at 21°C (70°F)



### TYPICAL DISCHARGE CHARACTERISTICS Average Performance at 21°C (70°F)



# 

**Description:** Rechargeable 1.2V

Chemical System: Nickel-Metal Hydride (NiMH)

**Designation:** ANSI-1.2H1 **Battery Voltage:** 1.2 Volts

Average Capacity: 850 mAh (to 1.0 volts)

(Based on 170 mA (0.2C) discharge rate)

Average Weight: 12.0 grams (0.4 oz.)

**Volume:** 3.8 cubic centimeters (0.2 cubic inch)

Jacket: Plastic Label

#### **Internal Resistance**

The internal resistance of the cell varies with state of charge, as follows:

Cell Charged
100 milliohms
1200 milliohms
(tolerance of ±20% applies to above values)

#### AC Impedance (No Load)

The impedance of the charged cell varies with frequency, as follows:

Frequency (Hz) Impedance (milliohms

(Charged Cell)

35

Note: Above values based on AC current set at 1.0 ampere. Value tolerances are ±20%

### **Operating and Storage Temperatures**

1000

Ranges of temperature applicable to operation of the NH12 cells are:

Charge @ 0.1C: 32°F to 122°F (0°C to 50°C)

Discharge @ 0.1C: -4°F to 122°F (-20°C to 50°C)

Storage: - 40°F to 122°F (-40°C to 50°C)

( 6 Months Max. )

- 4°F to 95°F (-20°C to 35°C)

(2 Years Max.)

Operating at extreme temperature will significantly affect service and cycle life.

### **Important Notice**

This data sheet contains information specific to batteries manufactured at the time of its publication.

Contents herein do not constitute a warranty.

Copyright © Eveready Battery Co. Inc. - All Rights Reserved