

# PRODUCT SPECIFICATION

#### 1. SCOPE

This specification describes the electrical, mechanical and environmental parameters for this battery pack consisting of a Lithium Ion cell 3.7V/ 1960 mAh, with protection safety circuit.

#### 2. Dimensions:


- Thickness =10.9 mm
- Width =38.23 mm
- Length = 52 mm
- **3. Weight**: 0.105 lb

### 4. Cell specification: Li- Ion Battery. 1S1P

- 4.1 Nominal voltage: 3.7V
- 4.2 Capacity: Nominal 1960mAh at 23°C using:
  - Charge profile of 4.2V
  - Recommended charge current of 1330mA
  - Charging time of 3 hrs or a taper current of 40mA (C/20)
  - Discharge profile with a maximum current of 380mA (C/5) to 3.0V

### 4.3 Charging the Battery:


# Lithium Ion Charging Characteristics



### 4.3.1 Charging Condition:

- CV of 4.2V max
- CC of 2200mA max.

REVISION 00	ECR/ECN INFORMATION EC No: DATE:	TITLE:	3.7V 1960mAh Li-Ion ba	nttery	SHEET No. 1 of 3
DOCUMENT NUMBER: 990456D		CREATE	D/REVISED BY: AIE	CHECKED BY MJS	APPROVED BY MJS





# PRODUCT SPECIFICATION

4.3.2 To charge lithium-ion battery packs please follow the charging instruction stated below:

#### Charging instructions

- Charge Voltage: Limit the maximum charge voltage to 4.2V times the number of cells connected in series. This charging voltage is noted on the product specification sheet.
- Charge current: Packs should be charged at C rate for lithium-ion cells. C is the nominal capacity of the pack. (Example: for a 2400 mAh cell, charge at 2.4A).
- Pre-charge: If the cells are deeply depleted (less than 2.9V per cell), packs should be charged at 10% of their capacity (Example: for a 2400 mAh cell, charge at 240 mA) until reaching 3.0V per cell when charging can be continued as stated above.
- Charge temperature: Do not charge lithium ion cells at less than 0°C or more than 45°C.
- Reverse polarity: When connecting the cells to a charger, verify proper polarity.
- Charge method: Lithium ion cells should be charged using a constant current/constant voltage (CC/CV) method. Apply the charge current as stipulated above in step 2 until the pack reaches the voltage measured in step 1. Then, hold the voltage constant until the current tapers down to about 5% of nominal capacity (Example: for a 2400 mAh cell, charge until current is 120 mA).

## 4.4 Discharge condition:

- Cutoff voltage of 3.0V
- Maximum discharge current of 1800mA.
- 4.5 Cycle life: 80% of initial minimum capacity after 500 cycles at 0.2C, 23°C

#### 4.6 Temperature:

- Charge 0~45°C
- Discharge -20~60°C
- Storage -20~20°C
- 4.7 Products shipped have 40% state of charge typical

REVISION 00	ECR/ECN INFORMATION EC No: DATE:	TITLE:	3.7V 1960mAh Li-Ion ba	attery	SHEET No. 2 of 3
DOCUMENT NUMBER: 990456D		CREATE	D/REVISED BY: AIE	CHECKED BY MJS	APPROVED BY MJS



# PRODUCT SPECIFICATION

# 5. Protection Safety Circuit

- Main IC controller is Mitsumi MM3099EYRE
- Overcharge cutoff voltage: 4.275V +/-20mV
- Overdischarge cutoff voltage: 2.30V +/- 35mV
- Overcurrent detection will not occur below 1.8A and will occur above 4.2A
- Thermistor 10k,5%
- Gold-Plated Contacts

# 6. Additional component

- Polyester Label
- Polycarbonate ABS Plastic Tray
- Polycarbonate ABS Plastic Cover
- Nomex, Kapton Tape, PVC Heat Shrink, or similar insulators

#### 7. Storage temperature and Humidity range

- -20-20°C,45-85%RH (within 1year)
- -20~45°C,45-85%RH (within 3 month)
- -20~60°C,45-85%RH (within 1 month)

#### 8. Storage cautions

- Do not store packs in places of high temperature or under direct sunlight
- For long term storage, store packs in 30% charge state.
- Do not store packs in place which may expose them to rain, water or high humidity.

REVISION 00	ECR/ECN INFORMATION EC No: DATE:	TITLE:	3.7V 1960mAh Li-Ion ba	attery	SHEET No. 3 of 3
DOCUMENT NUMBER: 990456D		CREATE	D/REVISED BY: AIE	CHECKED BY MJS	APPROVED BY MJS