




# DATA SHEET

#### Product Number: 694-93-624-00-670000







## **Description:**

**DIP Carrier** Disposable Metal Carrier with Ultra Low Profile Receptacles Closed Frame Through Hole Accepts .015-.021" Leads

**Plating Code:** 

93

**Shell Plating:** 

200 μ" Tin/Lead(93/7) over 100 μ" Nickel

**Inner Contact Plating:** 30 μ" Gold over 50 μ" Nickel

Packaging:

Packaged in Tubes

# Of Pins	A	В	С	Qty. per Tube	Mill-Max Part Number	RoHS Compliant
24	1.2	0.6	0.7	16	694-93-624-00-670000	NO

#### **CONTACT:**

Contact Used: #11, Standard 3 Finger Contact

Current Rating = 3 Amps

BERYLLIUM COPPER ALLOY 172 (UNS C17200) per ASTM B 194

### **Properties of BERYLLIUM COPPER:**

Chemical composition: Cu 98.1%, Be 1.9%

Temper as stamped: TD01

Properties after heat treatment (TH01):

• Hardness: 36-43 Rockwell C

Mechanical Life: 100 Cycles Min.

Density: .298 lbs/in3


Electrical Conductivity: 22% IACS\*

Resistance: 10 miliohms Max

Operating Temperature: -55°C/+125°C

Melting point: 980°C/865°C (liquidus/solidus)

Stress Relaxation†: 96% of stress remains after 1,000 hours @ 100 °C; 70% of stress remains after 1,000 hours @ 200 ٥C



†Since BeCu loses its spring properties over time at high temperatures; it is rated for continuous use up to 150°C. For applications up to 300°C, Mill-Max offers many contacts in Beryllium Nickel. Contact Tech Support for more info.

<sup>\*</sup>International Annealed Copper Standard, i.e. as a % of pure copper.

#### **LOOSE PIN:**

Loose Pin Used: 0552

BRASS ALLOY (UNS C36000) per ASTM B 16

#### **Properties of BRASS ALLOY:**

• Chemical composition: Cu 61.5%, Zn 35.4%, Pb 3.1%†

• Hardness as machined: 80-90 Rockwell B

• Density: .307 lbs/in3

• Electrical conductivity: 26% IACS\*

• Melting point: 900°C/885°C (liquidus/solidus)

 $\pm$  (3 to 4% lead is used to permit "free machining" and is permitted by EC Directive 2002/95Annex 6; so all pin materials are RoHS compliant)

## **INSULATOR INFORMATION:**

<sup>\*</sup>International Annealed Copper Standard, i.e. as a % of pure copper.