

Microwave Ceramics and Modules

Filter

2-Pol Filter for GPS

B69812N1577C303

Datasheet Standard



Features

- SMD filter consisting of coupled resonators with stepped impedances
- (NdBa)TiO₃ (ε_r = 88 / TC_f =0±10 ppm/K) with a coating of copper (10 μ m) and tin (>5 μ m)
- Excellent reflow solderability, no migration effect due to copper/tin metallization

Index

- Page 2 Component drawing
 - Recommended footprint
- Page 3 Characteristics
 - Maximum ratings
 - Typical passband characteristic
- Page 4 Processing information
 - Soldering requirements
 - Delivery mode

ISSUE DATE	14.05.03	ISSUE	В	PUBLISHER	SAW MWC PD F	PAGE	1/4
------------	----------	-------	---	-----------	--------------	------	-----




Microwave Ceramics and Modules


Filter

2-Pol Filter for GPS

B69812N1577C303


Datasheet Standard Component drawing





View from below onto the solder terminals and view from beside

Recommended footprint



FPS2T211.DOC

ISSUE DATE 14.05.0	ISSUE B	PUBLISHER	SAW MWC PD F	PAGE	2/4
--------------------	---------	-----------	--------------	------	-----



Microwave Ceramics and Modules	Filter
2-Pol Filter for GPS	B69812N1577C303

Datasheet Standard


Characteristics

		min.	typ.	max.	
Center frequency	f_{C}	-	1575	-	MHz
Insertion loss	α_{IL}		2.9	3.2	dB
Passband	В	3.0			MHz
Amplitude ripple (peak - peak)	Δα		0.2	0.5	dB
Standing wave ratio SI	WR		1.5	2.0	
Impedance	Z		50		Ω
Attenuation at < 1490 MHz at 1525 MHz at 1625 MHz	α	30 18 16	35		dB dB dB

Maximum ratings

IEC climatic category (IEC 68-1)		- 40/+ 90/56	
Operating temperature	T_{op}	0 / + 55	°C

Typical Passband Characteristics



18	ISSUE DATE	14.05.03	ISSUE	В	PUBLISHER	SAW MWC PD F	PAGE	3/4	
----	------------	----------	-------	---	-----------	--------------	------	-----	--



Microwave Ceramics and Modules

Filter

2-Pol Filter for GPS B69812N1577C303

Datasheet Standard

Processing information


ZNr.: 668 (FILT95 2)

Wettability to IEC 68-2-58: ≥ 75% (after aging)

Soldering requirements

Soldering type	reflow	
Maximum soldering temperature (measuring point on top surface of the component)	235 (max. 2 sec.) 225 (max. 10 sec.)	°C °C


Recommended soldering conditions (infrared):



LOETPROF.DOC

Delivery mode

- Blister tape to IEC 286-3, polyester, grey
- Pieces/tape: 3000



© EPCOS AG 2001. All Rights Reserved. Reproduction, publication and dissemination of this data sheet, enclosures hereto and the information contained therein without EPCOS' prior express consent is prohibited.

The information contained in this data sheet describes the type of component and shall not be considered as guaranteed characteristics. Purchase orders are subject to the General Conditions for the Supply of Products and Services of the Electrical and Electronics Industry recommended by the ZVEI (German Electrical and Electronic Manufacturers' Association), unless otherwise agreed.