



[United States](#) > [Products & Services](#) > [Manufacturing & Industry](#) > [Oil & Gas Industry Solutions](#) > [Product Catalog](#)

[Product Catalog for 3M Oil and Gas Industry](#) > [Mechanical Maintenance](#) > [3M™ Adhesives](#) > [3M™ Scotch-Weld™ Epoxy Adhesive DP-110 Translucent](#) >

3M™ Scotch-Weld™ Epoxy Adhesive DP110 Translucent Duo-Pak, 1.7 fl oz, 12 per case



Colorless, fast setting, flexible, two-part adhesive with a 1:1 mix ratio for bonding many materials, such as metals, ceramics and many plastics. 9 minute worklife with handling strength in 20 minutes.

Unlike many other fast cure two-part epoxies, this adhesive has excellent peel strength and shock and impact resistance. NOTE: Make-To-Order with a lead time of 30-45 days.

Products

Product / 3M Id / UPC

3M™ Scotch-Weld™ Epoxy Adhesive DP110 Translucent Duo-Pak, 1.7 fl oz, 12 per case

3M Id : 62-3563-1434-4

GTIN(UPC/EAN) : 0 00 21200 82465 4

3M

Scotch-Weld™

Epoxy Adhesive

DP110 Translucent and Gray

Technical Data

Product Description 3M™ Scotch-Weld™ Epoxy Adhesive DP110 Translucent and Gray are two-part epoxy adhesives which combine a fast cure with flexibility.

- Features**
- Controlled flow
 - 20 minute handling strength
 - Duo-Pak cartridge dispensing system
 - Good adhesion to many plastics and metals

Typical Uncured Physical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Product		Scotch-Weld Epoxy Adhesive DP110 Translucent	Scotch-Weld Epoxy Adhesive DP110 Gray
Viscosity @ 72°F (23°C), 73°F (24°C) (CPS)	Base Accelerator	30,000 - 70,000 30,000 - 70,000	40,000 - 90,000 40,000 - 90,000
Base Resin	Base Accelerator	Modified Epoxy Amine	Modified Epoxy Amine
Color	Base Accelerator	Translucent White Light Yellow	White Black
Net Weight (Lbs./Gallon)	Base Accelerator	9.1 - 9.4 9.0 - 9.3	9.1 - 9.4 9.0 - 9.3
Mix Ratio B : A	Volume Weight	100 : 100 100 : 99	100 : 100 100 : 99
Worklife @ 73°F (24°C) (minutes)		8 - 13	8 - 13

Typical Cured Physical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Product	Scotch-Weld Epoxy Adhesive DP110 Translucent	Scotch-Weld Epoxy Adhesive DP110 Gray
Color	Yellow Translucent	Gray
Shore D Hardness (approx.)	40	45
Elongation (approx.)	40%	40%

Scotch-Weld™

Epoxy Adhesives

DP110 Translucent and Gray

Typical Cured Thermal Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Product	3M™ Scotch-Weld™ Epoxy Adhesive DP110 Translucent	3M™ Scotch-Weld™ Epoxy Adhesive DP110 Gray
Thermal Conductivity BTU/Hr/Ft ² /°F/Ft.	.106 @ 113°F (45°C)	.104 @ 113°F (45°C)
Thermal Coefficient of Expansion -58°F (-50°C) - 32°F (0°C) -58°F (-50°C) - 166°F (110°C)	80 x 10 ⁻⁶ 200 x 10 ⁻⁶	73 x 10 ⁻⁶ 165 x 10 ⁻⁶
Glass Transition Temp.	55°F (13°C)	61°F (16°C)

Typical Cured Electrical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Product	Scotch-Weld Epoxy Adhesive DP110 Translucent	Scotch-Weld Epoxy Adhesive DP110 Gray
Dielectric Strength (volts/mil)	520	470
Volume Resistivity (ohms - cm)	4.5 x 10 ¹⁰	6.9 x 10 ¹⁰

Typical Adhesive Performance Characteristics

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

The following product performance data was obtained in the 3M laboratory under the conditions specified. The following data show typical results obtained with Scotch-Weld epoxy adhesive DP110 Translucent and Gray when applied to properly prepared substrates and cured for 48 hours at 73°F (23°C) under 2 psi pressure and tested according to the specifications indicated.

Note: All data developed after a 48 hour cure @ 75°F (24°C) under 2 psi pressure unless noted otherwise.

A. Aluminum Overlap Shear

Overlap shear strength was measured on FPL etched 1 in. wide by 1/2 in. overlap specimens. The bonds were made from 2 panels of 4 in. x 7 in. x .063 in., 2024 T3 clad aluminum bonded together and cut into 1 in. wide specimens. The separation rate of the testing jaws was .1 in./minute. Tests similar to ASTM D-1002.

Test Temp	Scotch-Weld Epoxy Adhesive DP110 Translucent	Scotch-Weld Epoxy Adhesive DP110 Gray
-67°F (-55°C)	2500 psi	2700 psi
75°F (24°C)	2500 psi	3500 psi
160°F (71°C)	270 psi	270 psi
180°F (82°C)	200 psi	250 psi

Scotch-Weld™

Epoxy Adhesives

DP110 Translucent and Gray

Storage	Store products at 60-80°F (16-27°C) for maximum storage life.
Shelf Life	3M™ Scotch-Weld™ Epoxy Adhesive DP110 Translucent and Gray have a shelf life of 15 months in their unopened containers. Duo-pak cartridges have a shelf life of two years in their unopened bulk containers.
Precautionary Information	Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.
For Additional Information	To request additional product information or to arrange for sales assistance, call toll free 1-800-362-3550 or visit www.3M.com/adhesives . Address correspondence to: 3M Industrial Adhesives and Tapes Division, Building 21-1W-10, 900 Bush Avenue, St. Paul, MN 55144-1000. Our fax number is 651-778-4244. In Canada, phone: 1-800-364-3577. In Puerto Rico, phone: 1-787-750-3000. In Mexico, phone: 52-70-04-00.
Product Use	All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.
Warranty and Limited Remedy	Unless stated otherwise in 3M's product literature, packaging inserts or product packaging for individual products, 3M warrants that each 3M product meets the applicable specifications at the time 3M ships the product. Individual products may have additional or different warranties as stated on product literature, package inserts or product packages. 3M MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's application. If the 3M product is defective within the warranty period, your exclusive remedy and 3M's and seller's sole obligation will be, at 3M's option, to replace the product or refund the purchase price.
Limitation of Liability	Except where prohibited by law, 3M and seller will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.



This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.



Industrial Business
Industrial Adhesives and Tapes Division



Material Safety Data Sheet

Copyright, 2007, 3M Company. All rights reserved. Copying and/or downloading of this information for the purpose of properly utilizing 3M products is allowed provided that: (1) the information is copied in full with no changes unless prior written agreement is obtained from 3M, and (2) neither the copy nor the original is resold or otherwise distributed with the intention of earning a profit thereon.

SECTION 1: PRODUCT AND COMPANY IDENTIFICATION

PRODUCT NAME: 3M(TM) Scotch-Weld(TM) Epoxy Adhesive DP-110, Translucent (Part B)
MANUFACTURER: 3M
DIVISION: Industrial Adhesives and Tapes Division

Issue Date: 02/07/2007
Supersedes Date: 05/29/2001

Document Group: 11-3315-6

Product Use:

Specific Use: Part B of 2-Part Epoxy Adhesive
Intended Use: Industrial use

SECTION 2: INGREDIENTS

<u>Ingredient</u>	<u>C.A.S. No.</u>	<u>% by Wt</u>
Epoxy Resin	25068-38-6	60 - 100
Methacrylate/Butadiene/Styrene Polymer	25053-09-2	10 - 30
Hydrogenated Terphenyl	Trade Secret	5 - 10
Amorphous Silica	67762-90-7	0.5 - 1.5
Hydrogenated Polyphenyls	Trade Secret	0.5 - 1.5

SECTION 3: HAZARDS IDENTIFICATION

3.1 EMERGENCY OVERVIEW

Specific Physical Form: Paste

Odor, Color, Grade: Translucent, slight odor.

General Physical Form: Liquid

Immediate health, physical, and environmental hazards: May cause allergic skin reaction.

3.2 POTENTIAL HEALTH EFFECTS

SECTION 8: EXPOSURE CONTROLS/PERSONAL PROTECTION

8.1 ENGINEERING CONTROLS

Provide appropriate local exhaust for cutting, grinding, sanding or machining. Use general dilution ventilation and/or local exhaust ventilation to control airborne exposures to below Occupational Exposure Limits and/or control dust, fume, or airborne particles. If ventilation is not adequate, use respiratory protection equipment. Provide ventilated enclosure for heat curing. If exhaust ventilation is not available, use appropriate respiratory protection.

8.2 PERSONAL PROTECTIVE EQUIPMENT (PPE)

8.2.1 Eye/Face Protection

Avoid eye contact.

The following eye protection(s) are recommended: Safety Glasses with side shields, Indirect Vented Goggles.

8.2.2 Skin Protection

Avoid skin contact.

Select and use gloves and/or protective clothing to prevent skin contact based on the results of an exposure assessment. Consult with your glove and/or protective clothing manufacturer for selection of appropriate compatible materials.

Gloves made from the following material(s) are recommended: Neoprene, Nitrile Rubber, Polyethylene/Ethylene Vinyl Alcohol.

8.2.3 Respiratory Protection

Avoid breathing of vapors, mists or spray. Avoid breathing of dust created by cutting, sanding, grinding or machining.

Select one of the following NIOSH approved respirators based on airborne concentration of contaminants and in accordance with OSHA regulations: Half facepiece or fullface air-purifying respirator with organic vapor cartridges and P95 particulate prefilters, Half facepiece or fullface air-purifying respirator with organic vapor cartridges and N95 particulate prefilters, Half facepiece or fullface air-purifying respirator with organic vapor cartridges and P100 particulate prefilters. Consult the current 3M Respiratory Selection Guide for additional information or call 1-800-243-4630 for 3M technical assistance.

8.2.4 Prevention of Swallowing

Do not eat, drink or smoke when using this product. Wash exposed areas thoroughly with soap and water.

8.3 EXPOSURE GUIDELINES

<u>Ingredient</u>	<u>Authority</u>	<u>Type</u>	<u>Limit</u>	<u>Additional Information</u>
Amorphous Silica	CMRG	CEIL	5 mg/m ³	
Hydrogenated Terphenyl	ACGIH	TWA	0.5 ppm	
Hydrogenated Terphenyl	OSHA	TWA	0.5 ppm	Table Z-1A

SOURCE OF EXPOSURE LIMIT DATA:

ACGIH: American Conference of Governmental Industrial Hygienists

CMRG: Chemical Manufacturer Recommended Guideline

OSHA: Occupational Safety and Health Administration

AIHA: American Industrial Hygiene Association Workplace Environmental Exposure Level (WEEL)

SECTION 9: PHYSICAL AND CHEMICAL PROPERTIES

Specific Physical Form:

Paste

Odor, Color, Grade:

Translucent, slight odor.

General Physical Form:

Liquid

Autoignition temperature	<i>No Data Available</i>
Flash Point	≥ 480 °F [<i>Test Method: Closed Cup</i>]
Flammable Limits - LEL	<i>Not Applicable</i>
Flammable Limits - UEL	<i>Not Applicable</i>
Boiling point	≥ 260 °C
Density	1.13 g/ml
Vapor Density	<i>Not Applicable</i>
Vapor Pressure	<i>Not Applicable</i>
Specific Gravity	1.13 [<i>Ref Std: WATER=1</i>]
pH	<i>Not Applicable</i>
Melting point	<i>No Data Available</i>
Solubility in Water	Nil
Evaporation rate	<i>Not Applicable</i>
Volatile Organic Compounds	0.0 %
Percent volatile	0.0 % volume
VOC Less H2O & Exempt Solvents	<i>Not Applicable</i>
Viscosity	45000 - 65000 centipoise [<i>@ 73.4 °F</i>]

SECTION 10: STABILITY AND REACTIVITY

Stability: Stable.

Materials and Conditions to Avoid: Strong oxidizing agents

Hazardous Polymerization: Hazardous polymerization will not occur.

Hazardous Decomposition or By-Products

<u>Substance</u>	<u>Condition</u>
Aldehydes	During Combustion
Hydrocarbons	During Combustion
Carbon monoxide	During Combustion
Carbon dioxide	During Combustion
Ketones	During Combustion
Toxic Vapor, Gas, Particulate	During Combustion

SECTION 11: TOXICOLOGICAL INFORMATION

Please contact the address listed on the first page of the MSDS for Toxicological Information on this material and/or its components.

SECTION 12: ECOLOGICAL INFORMATION

ECOTOXICOLOGICAL INFORMATION

Not determined.