

EVEREADY BATTERY COMPANY, INC.

www.energizer.com


1-800-383-7323 / CANADA - USA + 44 (0) 208 920 2306 / EUROPE



ENERGIZER NO. CR2016

Industry Standard Dimensions

mm (inches)



0.20 (0.008) Maximum Ref. Permissible deflection from a flat.

Simulated Application test

Typical Performance at 21°C (70°F)

Schedule:	Typical Drains:	Load	Cutoff
	at 2.9V		2.0V
	(mA)	(ohms)	(hours)
Continuous	0.097	30,000	928

Typical Discharge Characteristics

Load: 30K ohms - Continuous Typical Drain @ 2.9V: 0.097 mA



Classification: "Lithium Coin"

Chemical System: Lithium / Manganese Dioxide (Li/MnO₂) Designation: ANSI / NEDA-5000LC, IEC-CR2016

Specifications

Nominal Voltage: 3.0 Volts

Typical Capacity: 90 mAh (to 2.0 volts)

(Rated at 30K ohms at 21°C)

Typical Weight: 1.9 grams (0.07 oz.)

Typical Volume: 0.5 cubic centimeters (0.03 cubic inch)

Max Rev Charge: 1 microampere

Energy Density: 122 milliwatt hr/g, 464 milliwatt hr/cc

Typical Li Content: 0.036 grams (0.0013 oz.)

UL Listed: MH12454


Shipping: For complete details, please reference: Global (except US): Special Provision A45 of the International

Air Transport Association Dangerous

Goods Regulations

United States: 49 CFR 173.185

Cross Section



Internal resistance Characteristics

Pulse Test at 21°C (70°F)

Bkgnd Drain: Continuous


30K ohms

0.097 mA @2.9V

Pulse Drain: 2 seconds X 12 times/day

400 ohms

6.8 mA @2.7V



Important Notice

This data sheet contains typical information specific to batteries manufactured at the time of its publication.

Contents herein do not constitute a warranty.

© Eveready Battery Company, Inc. - All Rights Reserved

Form No. FBC - 4118F Page 1 of 1