

RTV Silicones by  **MOMENTIVE**  
performance materials  
**1-Part Adhesive Sealant RTV133**



**Primary Characteristics**

- ▶ [Black paste](#)
- ▶ [Non-corrosive](#)
- ▶ **Flame retardant**
- ▶ [Alkoxy cure](#)
- ▶ [UL V-1 and V-0 Recognition](#)
- ▶ [UL File No. E36952](#)

Use RTV133 as a flame retardant coating - as a sealant on firewalls, switching devices, motors and high voltage transformers.

**Available Sizes**

Catalog Number	Sizes Available	Description
RTV133-300ML	300 mL (10 oz)	Cartridge

**Specifications**

Use	Adhesive Sealant
Special Feature	Flame retardant
Standards	UL V-1 and V-0 recognition
Cross Reference	RTV133
<b>Uncured Properties</b>	
Consistency	Paste
Color	Black
Specific Gravity	1.23
Tack Free Time	1 hour
Useful Temp. Range	-60°C to 205°C (-75°F to 400°F)
<b>Cured Properties - MECHANICAL</b>	
<a href="#">Hardness</a>	46 (Shore A)
Tensile Strength	4.51 MPa (650 psi)
Elongation	250%
<b>Cured Properties - ELECTRICAL</b>	
Dielectric Strength	20 kV/mm (500 V/mil)
Dielectric Constant	2.8 @ 100 Hz
<b>Other</b>	
<a href="#">Viscosity</a> (@ 25°C)	650 g/min