

Fine-L-Kote[™] SR

Silicone Conformal Coating 2102

Introduction

A type SR silicone resin conformal coating that has excellent moisture and fungus resistance properties and is UL recognized (UL File Number E95150). Material flexibility allows for vibration, movement, and rapid changes in temperature. Fine-L-Kote[™] SR is a durable coating that offers chemical resistance and is recommended for harsh environments. Contains Opti/Scan[™] to allow for black light inspection. Coated boards can be reworked by applying soldering iron directly to coating. Coated boards can be stripped using Trace Technologies[™] Conformal Coating Remover (2510-N, 2510-P).

Features / Benefits

Moisture, Thermal and Chemical Resistant UL Recognized Recommended for Harsh Environments Flexible Contains Opti/Scan™

Chemical Components

| 4-5% - Aerosol |
|------------------|
| 7-8% - Bulk |
| 28-30% - HV |
| <1% |
| 12-15% |
| 40-50% - HV |
| |
| <4% - Aerosol |
| 3-6% - Bulk, HV |
| 20-25% - Aerosol |
| 45-50% - Bulk |
| 10-30% - Aerosol |
| 10-12% |
| 7-10% - HV |
| |

| Cure Type | Thermal | | |
|--|------------------------|------------------------|------------------|
| Meets/Exceeds IPC-CC-830 MIL-I-46058C | SR Silicone | | |
| Thermal Shock | 5 | | |
| Dielectric Constant (@ 10 ⁶ Hz) | 2.33 | | |
| Dielectric Strength (Volts/Mill) | 1100 Dry | 976 Wet | |
| Volume Resistivity | 1x10 ¹⁴ Dry | 9x10 ¹⁴ Wet | |
| Moisture Resistance | 5 | | |
| Resistant to Fungus | Yes | | |
| Ease of Repair | 5 | | |
| Flexibility | 5 | | |
| Chemical Resistance | 4 | | |
| Dry Time to Touch | 1 Hour | | |
| Cure Time | 72 Hours | | |
| Accelerated Cure Time | 30 min. @ 90°F | 45 min. @ 200°F | Two Step Process |
| Removal (2510-P or 2510-N) | 1-5 min. | | |
| Burn Through | Yes | | |

Ratings: 5 (Excellent), 4 (Very Good), 3 (Good), 2 (Fair), 1 (Poor)

Typical Properties as Cured Physical Properties for 2102

| Operating temperature range °C | -65 to 200 |
|--|--------------|
| Specific Gravity @ 25°C | 1.11 |
| Tensile Strength @ 25°C, psi | 600 |
| Elongation @ 25°C percent | 60 |
| Durometer Hardness, Shore D, points | 25 |
| Volume Coefficient of Thermal Expansion um/m/c | 253.6 |
| Thermal Conductivity @ 100°C Watts/mK | 0.17 |
| Water Absorption, 100 hours @ 25°C Percent | 0.05 |
| Viscosity (cps) Bulk / HV | 4-10 / 60-90 |

Environmental Policy

Techspray® is committed to developing products to ensure a safer and cleaner environment. We will continue to meet and sustain the regulations of all federal, state and local government agencies.

Packaging and Availability

Fine-L-Kote[™] SR may be ordered in the following container sizes:

| 2102-12S | 12 Ounce Aerosol |
|----------|--------------------|
| 2102-P | 1 Pint in Glass |
| 2102-G | 1 Gallon in Metal |
| 2102-GHV | 1 Gallon in Metal |
| 2102-5G | 5 Gallons in Metal |
| | |

| Fine-L-Kote™ Part Number | 2102 | 2103 | 2104 | 2106 |
|--|---|--|--|-------------------------------------|
| Cure Type | Thermal | Thermal | Thermal | Thermal |
| Meets / Exceeds IPC-CC-830 MIL-I-46058C | SR Silicone | AR Acrylic | UR Urethane | SR Silicone |
| Thermal Shock | 5 | 2 | 3 | 5 |
| Dielectric Constant (6 10 ¹ Hz) | 2.66 | 3.1 | 3.80 | 2.5 |
| Dielectric Strength (Volts/Mil) | 1100 Dry 976 Wet | 2086 | 380 | 560 |
| Volume Resistivity | 1x10 ¹⁴ Dry 9x10 ¹⁴ Wet | 4x1013 Dry | 2x10 ¹³ | 5x10 ¹³ |
| Moisture Resistance | 5 | 5 2 | | 5 |
| Resistant to Fungus | Yes | Yes | Yes | Yes |
| Ease of Repair | 3 | 5 | 2 | 3 |
| Flexibility | 5 | 2 | 3 | 5 |
| Chemical Resistance | 4 | 1 | 4 | 2 |
| Dry Time To Touch | 1 Hour | 15 Min. | 15 Min. | 45 Min. |
| Cure Time | 72 Hours | 24 Hours | 24 Hours | 24 Hours |
| Accelerated Cure Time | 30 min. @ 90'F 45 min. @ 200'F Two Step Process | 20 min. @ 120'F 30 min. @ 180'F Two Step Process | 20 min. @ 120'F 30 min. @ 180'F Two Step Process | 15 min. @ 120'F One Step Process |
| *Removal (2510) | 1-5 min. | 1-5 min. | 1-5 min. | 1-5 min. |
| Burn Through | Yes | Yes | Yes | Yes |
| Ratings: 5 - Excellent, 4 - Very Good, 3 - Good, 2 - Fain, 1 - Poon * Available: Conformal Coating Rer All coatings may be thinned by using Fine-L-Kote TM UR Thinner (2105) * Product #'s: 2510-P and 2510-N MOISTURE RESISTANT CHEMICAL RESISTANT CHEMICAL RESISTANT | | | | |
| $ \begin{array}{c ccccccccccccccccccccccccccccccccccc$ | | | | |

Copyright 2004 Tech Spray, L. P. For Commercial Use Only

MATERIAL SAFETY DATA SHEET

Finished Product



MSDS Ref. No: 2102-P

Fine-L-Kote[™] SR

1. PRODUCT AND COMPANY IDENTIFICATION

PRODUCT NAME: Fine-L-Kote[™] SR **PRODUCT DESCRIPTION:** Silicone Conformal Coating **PRODUCT CODE:** 2102-P **PRODUCT FORMULATION NAME:** Fine-L-Coat[™] SR

MANUFACTURER

Techspray, L.P.

2. COMPOSITION / INFORMATION ON INGREDIENTS

| Chemical Name | Content | CAS | EINECS |
|--|----------------|----------------|---------------|
| Acetone | 30 - 60 | 67-64-1 | 200-662- 2 |
| Hexane | 15 - 40 | 110-54-3 | 203-777- 6 |
| 1-(2-Methoxy-Methyl-Ethoxy)-2-Propanol Acetate | 1 - 10 | 88917-22- 0 | |
| Polysiloxane mixture | 8 - 20 | | |
| Benzene- methyl, (Toluene) | 1 - 6 | 108-88-3 | 203-625- 9 |

EEC LABEL SYMBOL AND CLASSIFICATION

۲

R12 - Extremely flammable.

EEC Extremely flammable - "F+"



R20/21/22 - Harmful by inhalation, in contact with skin and if swallowed.

EEC Harmful - "Xn"

3. HAZARDS IDENTIFICATION

EMERGENCY OVERVIEW

PHYSICAL APPEARANCE: Transparent, colorless liquid.

IMMEDIATE CONCERNS: Flammable liquid and vapor.

POTENTIAL HEALTH EFFECTS

EYES: Substance causes substantial eye irritation.

SKIN: Prolonged or repeated contact can result in defatting and drying of the skin which may result in skin irritation and dermatitis (rash).

INGESTION: Harmful if swallowed.

INHALATION: High concentrations in immediate area can displace oxygen and can cause dizziness, unconsciousness, and possibly death with longer exposure. Keep people away from such vapors without self-contained breathing apparatus.

SIGNS AND SYMPTOMS OF OVEREXPOSURE

EYES: Symptoms of overexposure include: stinging, tearing, redness and pain.

INGESTION: For large amounts; abdominal pain, nausea and vomiting.

4. FIRST AID MEASURES

EYES: Immediately flush eyes with plenty of water for at least 15 minutes. Get immediate medical attention.

SKIN: Wash with soap and water. Get medical attention if irritation develops or persists.

INGESTION: Aspiration hazard. If swallowed, vomiting may occur spontaneously, but do not induce. If vomiting occurs, keep head below hips to prevent aspiration into lungs. Call a physician immediately.

INHALATION: Remove to fresh air. If not breathing, give artificial respiration or give oxygen by trained personnel. Seek immediate medical attention.

5. FIRE FIGHTING MEASURES

FLASHPOINT AND METHOD: -12.2°C (10°F)TAG CC

FLAMMABLE LIMITS: 1.8% to 10%

GENERAL HAZARD: Flammable Liquid. Can release vapors that form explosive mixtures at temperatures at or

| STEL | NL ppm | NL mg/ m3 | NL ppm | NL mg/ m3 | NL ppm | NL mg/ m3 |
|------|----------------------------|-----------------------------------|--|--|--|---|
| | | | | | | |
| | | | | | | |
| TWA | 200 ppm | 375 mg/ m3 | s 50 ppm ^[2] | 188 mg/ m3 | NL | NL |
| STEL | C300 ppm ^[3] | 560 mg/ m3 | / NL ppm | NL mg/ m3 | NL | NL |
| | | | | | | |
| | TWA | TWA ²⁰⁰ _{ppm} | STEL ppm m3 TWA 200 375 mg/ ppm m3 | STEL ppm m3 ppm TWA 200 ppm 375 mg/ S 50 m3 50 ppm ^[2] | STEL ppm m3 ppm m3 TWA 200 ppm 375 mg/ S 50 m3 188 mg/ ppm ^[2] | STEL ppm m3 ppm m3 ppm 200 375 mg/ \$ 50 188 mg/ |

1. NL = Not Listed**2.** S = Skin

3. C = Ceiling

ENGINEERING CONTROLS: Local exhaust ventilation may be necessary to control any air contaminants to within their TLVs during the use of this product.

PERSONAL PROTECTIVE EQUIPMENT

EYES AND FACE: For normal conditions, wear safety glasses. Where there is reasonable probability of liquid contact, wear splash-proof goggles.

SKIN: The glove(s) listed below may provide protection against permeation. Gloves of other chemically resistant materials may not provide adequate protection. Viton, Solvex, Butyl, Buna, Neoprene.

RESPIRATORY: A respiratory protection program that meets OSHA 1910.134 and ANSI Z88.2 requirements must be followed whenever workplace conditions warrant a respirator's use.

9. PHYSICAL AND CHEMICAL PROPERTIES

PHYSICAL STATE: Liquid **pH:** Not Applicable PERCENT VOLATILE: 86 at 20°C (68°F) **BOILING POINT:** 79°C (134°F) **SOLUBILITY IN WATER:** Insoluble **SPECIFIC GRAVITY:** 0.83 (water=1) (VOC): 481 g/L (non-exempt VOC)

10. STABILITY AND REACTIVITY

STABLE: YES

HAZARDOUS POLYMERIZATION: NO

CONDITIONS TO AVOID: Heat, flames, ignition sources, and incompatables.

STABILITY: Stable.

INCOMPATIBLE MATERIALS: Concentrated nitric and sulfuric acid mixtures, chloroform, alkalis, chlorine compounds, acids, potassium t-butoxide.

11. TOXICOLOGICAL INFORMATION

| INGREDIENT(S) Acetone | <u>ORAL LD ₅₀ (rat)</u> 5800 - mg/kg | DERMAL LD ₅₀ (rabbit) 20 - g/kg | <u>INHALATION LC ₅₀ (rat)</u> 50100 - ppm |
|--------------------------------|--|---|---|
| EYE EFFECTS: Not Available | | | |
| SKIN EFFECTS: Not Available | | | |
| CARCINOGENICITY: | | | |
| IARC: NOT listed | | | |
| NTP: NOT listed | | | |
| OSHA: NOT listed | | | |
| REPRODUCTIVE EFFECTS: 7 | Coluene is listed as a r | reproductive hazard. | |

12. ECOLOGICAL INFORMATION

ENVIRONMENTAL DATA: There is limited information available on the environmental fate and effects of this material. The primary environmental concern for release is the impact on aquatic and terrestrial species. Due care should be taken to avoid the accidental release of this material into the environment.

13. DISPOSAL CONSIDERATIONS

GENERAL COMMENTS: Dispose of in a manner consistent with federal, state, and local regulations.

14. TRANSPORT INFORMATION

DOT (DEPARTMENT OF TRANSPORTATION) PROPER SHIPPING NAME: CONSUMER COMMODITY ORM-D

ROAD AND RAIL (ADR/RID): KEMLER NUMBER: UN1993 HAZARD CLASS: 3

AIR (ICAO/IATA)
 PROPER SHIPPING NAME: Flammable Liquid, N.O.S., (Hexane, Acetone)
 UN/NA NUMBER: UN1993
 PRIMARY HAZARD CLASS/DIVISION: 3
 PACKING GROUP: II
 NOTE: Domestic shipments only. When shipping International contact TechSpray shipping department.

VESSEL (IMO/IMDG) PROPER SHIPPING NAME: Flammable Liquid, N.O.S., (Hexane, Acetone) UN/NA NUMBER: UN1993 PRIMARY HAZARD CLASS/DIVISION: 3 PACKING GROUP: II NOTE: Page 3230

CANADA TRANSPORT OF DANGEROUS GOODS PROPER SHIPPING NAME: CONSUMER COMMODITY ORM-D

15. REGULATORY INFORMATION

UNITED STATES

SARA TITLE III (SUPERFUND AMENDMENTS AND REAUTHORIZATION ACT)

311/312 HAZARD CATEGORIES:

FIRE: YES PRESSURE GENERATING: NO REACTIVITY: NO ACUTE: YES CHRONIC: YES

313 REPORTABLE INGREDIENTS: Toluene n-Hexane (110-54-3)

CERCLA (COMPREHENSIVE RESPONSE, COMPENSATION, AND LIABILITY ACT)

CERCLA REGULATORY: Acetone (67-64-1) Contains toluene (#108-88-3).

CERCLA RQ: 1000 Lbs.

TSCA (TOXIC SUBSTANCE CONTROL ACT)

TSCA STATUS: All components of this product are either listed or exempt from listing in the TSCA inventory.

RCRA STATUS: U220 U002

OSHA HAZARD COMM. RULE: Contents of this MSDS comply with the OSHA Hazard Communication Standard 29 CFR 1910.1200.

CANADA

WHMIS (WORKPLACE HAZARDOUS MATERIALS INFORMATION SYSTEM): This product has been classified according to the hazard criteria of the CPR. This MSDS contains all the information required by the CPR."

WHMIS CLASS: Class B2 - Flammable Liquids. Class D2B - Toxic Materials.

DOMESTIC SUBSTANCE LIST (INVENTORY): All components of this product are listed on the Canadian DSL.

EUROPEAN COMMUNITY

EEC LABEL SYMBOL AND CLASSIFICATION



R12 - Extremely flammable.

EEC Extremely flammable - "F+"