

RTV Silicones by MOMENTIVE 1-Part Adhesive Sealant RTV167



Primary Characteristics

- ▶ Light Gray Paste
- ▶ **High strength electronics**
- ▶ Non-corrosive
- ▶ Alkoxy neutral cure
- ▶ MIL-A-46146, group 1, type 1
- ▶ UL HB recognition
- ▶ UL File No. [E36952](#)

Excellent in areas that require an extra strength sealing and bonding. Non-corrosive to electronic metals, including copper and brass. Can be applied to vertical or overhead surfaces. Retains elastomeric properties for long periods at temperatures from -60°C to 205°C (75°F to 400°F) and for short periods up to 250°C (500°F). Excellent electrical insulating properties. This product meets Military spec. MIL-A-46146 and is UL HB recognized.

Available Sizes

Catalog Number	Sizes Available	Description	Case Qty
RTV167-85ML	85 mL (2.8 oz)	Tube	12
RTV167-300ML	▶ SPECIAL ORDER 300mL (10 oz)	Cartridge	24

Specifications

Use	Adhesive Sealant
Special Feature	High tensile strength
Standards	MIL-A-46146, group 1, type 1
	UL File no. E-36952
Cross Reference	RTV167
Uncured Properties	
Consistency	Paste
Color	Grey
Specific Gravity	1.12
Tack Free Time	4 hours
Cure through time	48 hours
Useful Temp. Range	-60°C to 205°C (-75°F to 400°F)
Cured Properties - MECHANICAL	
<u>Hardness</u>	37 (Shore A)
Tensile Strength	5.49 MPa (800 psi)
Elongation	600%
Peel Strength	10 kg/cm
	80 lb/in
Cured Properties - ELECTRICAL	
Volume Resistivity	3 x 10 ¹⁵ ohm · cm
Dielectric Strength	19.7 kV/mm
	500 V/mil

Dielectric Constant	2.8 @ 60 Hz
Cured Properties - THERMAL	
Thermal Conductivity	0.21 W/m · °K
Brittle Point	-60°C (-75°F)
Thermal Expansion	27 x 10 ⁻⁵ (°C) ⁻¹
Other	
<u>Viscosity</u> (@ 25°C)	180 g/min

© 2000 - 2007 MG Chemicals. All rights reserved.