

RTV Silicones by MOMENTIVE performance materials 1-Part Adhesive Sealant RTV102



Primary Characteristics

- ▶ White Paste
- ▶ High Strength
- ▶ High performance assembly
- Acetoxy cure
- ▶ Meets MIL-A-46106
- ▶ UL File no. E-36952
- FDA 21 CFR 177.2600

Excellent for insulating, sealing, bonding and formed-in-place gaskets. Can be applied to vertical and overhead surfaces. Not for use in delicate electrical and electronic applications in which corrosion of copper, brass, or other sensitive metals is undesirable. Can be used in food contact applications where FDA regulations apply. Reference CDS4319 "Food Contact Applications", "Silicone Rubber Compounds."

Available Sizes

Catalog No.	Size	Description
RTV102-85ML	2.8 oz	Tube
RTV102-300ML	10.1 oz	Cartridge

Specifications

Use	Adhesive Sealant
Special Feature	High tensile strength
Standards	FDA 21CFR 177.2600
	MIL-A-46106
	UL Recognized
	UL File No. E-36952
	UL 94 HB
Cross Reference	RTV 102, DC 732
Uncured Properties	
Consistency	Paste
Color	White
Specific Gravity	1.05
Tack Free Time	20 min
Cure Through Time (77°F / 50% relative humidity / 1/8" thick)	7 days
Cure Time (@ 77°F /50% relative humidity)	3 days
Useful Temp. Range	-60°C to 205°C (-75°F to 400°F)
Cured Properties - MECHANICAL	
<u>Hardness</u>	30 (Shore A)
Tensile Strength	2.8 kg/cm ² (400 psi)
Elongation	450%
Tear Strength	8 kg/cm
	45 lb/in

Downloaded from Elcodis.com electronic components distributor

Peel Strength	7 kg/cm	
	40 lb/in	
Cured Properties - ELECTRICAL		
Volume Resistivity	3 x 10 ¹⁵ ohm · cm	
Dielectric Strength	20 kV/mm	
	500 V/mil	
Dielectric Constant	2.8 @ 60 Hz	
Cured Properties - THERMAL		
Thermal Conductivity	0.5 x 10 ⁻⁴ cal/sec/cm ²	
Brittle Point	-60°C (-75°F)	
Thermal Expansion	7 x 10 ⁻⁵ (°C) ⁻¹	
Other		
Viscosity (@ 25°C)	400 g/min	

 $\ensuremath{\text{@}}$ 2000 - 2007 MG Chemicals. All rights reserved.