



EXCEPTIONALLY SOFT, HIGHLY COMPRESSIBLE GAP FILLER

Tflex™ 600 is an exceptionally soft, highly compressible gap filling interface pad with a thermal conductivity of 3 W/mK. These outstanding properties are the result of a proprietary boron nitride filler in the composition.

The high conductivity, in combination with extreme softness produces incredibly low thermal resistances.

While extremely soft, Tflex™ 600 recovers to over 90% of its original thickness after compression under low pressure. Tflex™ 600 is naturally tacky and requires no additional adhesive coating that can inhibit thermal performance. Tflex™ 600 is electrically insulating, stable from -45°C to 200°C and meets UL 94 V0 rating.

FEATURES AND BENEFITS

- Very high compressibility for low stress applications
- 3 W/mK thermal conductivity
- Available in thicknesses from 0.020" - 0.200" (0.5mm - 5.0mm)
- Naturally tacky, needs no further adhesive coating

APPLICATIONS

- Cooling components to the chassis or frame
- High speed mass storage drives
- RDRAM memory modules
- Heat pipe thermal solutions
- Automotive engine control units
- Telecommunications hardware

global solutions: local support.™

Americas: +1.800.843.4556

Europe: +49.8031.2460.0

Asia: +86.755.2714.1166

CLV-customerservice@lairdtech.com

www.lairdtech.com/thermal

	Tflex™ 620	Tflex™ 640	Tflex™ 660	Tflex™ 680	Tflex™ 6100	TEST METHOD
Construction & Composition	Reinforced boron nitride filled silicone elastomer	Boron nitride filled silicone elastomer	Boron nitride filled silicone elastomer	Boron nitride filled silicone elastomer	Boron nitride filled silicone elastomer	
Color	Blue-Violet	Blue-Violet	Blue-Violet	Blue-Violet	Blue-Violet	Visual
Thickness	0.020" (0.51mm)	0.040" (1.02mm)	0.060" (1.52mm)	0.080" (2.03mm)	0.100" (2.54mm)	
Thickness Tolerance	± 0.003" (± 0.08mm)	± 0.004" (± 0.10mm)	± 0.006" (± 0.15mm)	± 0.008" (± 0.20mm)	± 0.010" (± 0.25mm)	
Density	1.38 g/cc	1.34 g/cc	1.34 g/cc	1.34 g/cc	1.34 g/cc	Helium Pycnometer
Hardness	40 Shore 00	25 Shore 00	25 Shore 00	25 Shore 00	25 Shore 00	ASTM D2240
Tensile Strength	N/A	15 psi	15 psi	15 psi	15 psi	ASTM D412
% Elongation	N/A	75	75	75	75	ASTM D412
Outgassing TML (Post Cured)	0.13%	0.13%	0.13%	0.13%	0.13%	ASTM E595
Outgassing CVCM (Post Cured)	0.05%	0.05%	0.05%	0.05%	0.05%	ASTM E595
UL Flammability Rating	UL 94 V0	UL 94 V0	UL 94 V0	UL 94 V0	UL 94 V0	E180840
Temperature Range	-45°C to 200°C	-45°C to 200°C	-45°C to 200°C	-45°C to 200°C	-45°C to 200°C	ASTM D5470 (modified)
Thermal Conductivity	3 W/mK	3 W/mK	3 W/mK	3 W/mK	3 W/mK	
Thermal Impedance @ 10 psi @ 69KPa	0.46 °C-in ² /W 2.97 °C-cm ² /W	0.62 °C-in ² /W 4.00 °C-cm ² /W	0.85 °C-in ² /W 5.50 °C-cm ² /W	1.09 °C-in ² /W 7.04 °C-cm ² /W	1.23 °C-in ² /W 7.94 °C-cm ² /W	ASTM D5470 (modified)
Thermal Expansion	600 ppm/°C	430 ppm/°C	430 ppm/°C	430 ppm/°C	430 ppm/°C	IPC-TM-650 2.4.24
Breakdown Voltage	3,000 Volts AC	>5,000 Volts AC	>5,000 Volts AC	>5,000 Volts AC	>5,000 Volts AC	ASTM D149
Volume Resistivity	2 x 10 ¹³ ohm-cm	2 x 10 ¹³ ohm-cm	2 x 10 ¹³ ohm-cm	2 x 10 ¹³ ohm-cm	2 x 10 ¹³ ohm-cm	ASTM D257
Dielectric Constant @ 1MHz	3.31	3.31	3.31	3.31	3.31	ASTM D150

STANDARD THICKNESSES

0.020" (0.51mm)	0.030" (0.76mm)	0.040" (1.02mm)	0.050" (1.27mm)
0.060" (1.52mm)	0.070" (1.78mm)	0.080" (2.03mm)	0.090" (2.29mm)
0.100" (2.54mm)	0.110" (2.79mm)	0.120" (3.05mm)	0.130" (3.30mm)
0.140" (3.56mm)	0.150" (3.81mm)	0.160" (4.06mm)	0.170" (4.32mm)
0.180" (4.57mm)	0.190" (4.83mm)	0.200" (5.08mm)	

Consult the factory for alternate thicknesses

STANDARD SHEET SIZES

9" x 9" (229mm x 229mm)

18" x 18" (457mm x 457mm). 9" x 9" only over 0.100" thickness.

Tflex™ 600 can be die cut to individual shapes. Pressure sensitive adhesive is not applicable for Tflex™ 600 products.

TACKY ONE SIDE ONLY

Tflex™ 600 is naturally tacky on both sides. Tflex™ 600 can be provided tacky on one side only. This is indicated by the suffix "DC1".

This option offers good separation properties allowing the tacky side to stick to the heatsink/chassis/cold plate/etc. and the other "dry" side to release easily from the component(s).

REINFORCEMENT

Fiberglass is required in 0.020" (0.51mm) and 0.030" (0.76mm). Thicknesses of 0.040" (1.02mm) and above do not require reinforcement.

Data for design engineer guidance only. Observed performance varies in application. Engineers are reminded to test the material in application.

THR-DS-Tflex-600 0510

Any information furnished by Laird Technologies, Inc. and its agents is believed to be accurate and reliable. Responsibility for the use and application of Laird Technologies materials rests with the end user, since Laird Technologies and its agents cannot be aware of all potential uses. Laird Technologies makes no warranties as to the fitness, merchantability or suitability of any Laird Technologies materials or products for any specific or general uses. Laird Technologies shall not be liable for incidental or consequential damages of any kind. All Laird Technologies products are sold pursuant to the Laird Technologies Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2010 Laird Technologies, Inc. All Rights Reserved. Laird, Laird Technologies, the Laird Technologies Logo, and other marks are trade marks or registered trade marks of Laird Technologies, Inc. or an affiliate company thereof. Other product or service names may be the property of third parties. Nothing herein provides a license under any Laird Technologies or any third party intellectual property rights. A13512-00 Rev. J EO #9655, 05/2010.