TanFilm® Precision SIP Network Commercial and MIL Qualified Understein 10.10.PRF-83401 qualified 20.10.exton configuration available 20.10.exton configurati

The IRC 4700 Series is the ultimate combination of precision performance, reliability, and long term stability in a low profile,

TaNFilm[®] SIP package. Rugged welded lead construction combined with the inherent passivation characteristics of tantalum nitride insure superior ongoing performance over the installed life of the part.

Visit our website to view a graphical demonstration of IRC's TaNFilm reliability and performance features.

Electrical Data

Schematic	Resistance Range (Ω)	Absolute Tolerance	Ratio Tolerance	Absolute TCR (ppm/°C)	Tracking TCR (ppm/°C)	Element Power (mW)
C Commercial	49.9 - 99.9	F, G, J	F, G	±50; ±100; ±300	±20	
	100 - 200	B, D, F, G, J	D, F, G	±25; ±50; ±100; ±300	±15	100
	201 - 1.9K	B, D, F, G, J	B, D, F, G	±25; ±50; ±100; ±300	±10	120
	2.0K - 200K	B, D, F, G, J	A, B, D, F, G	±15; ±25; ±50; ±100; ±300	±5	
	20 - 49.9	F, G, J	F, G	±50; ±100; ±300	±20	
G Commercial	50.0 - 199	D, F, G, J	B, D, F, G	±25; ±50; ±100; ±300	±5	
	200 - 999	B, D, F, G, J	A, B, D, F, G	±25; ±50; ±100; ±300	±5	200
	1.0K - 100K	B, D, F, G, J	T, Q, A, B, D, F, G	±15; ±25; ±50; ±100; ±300	±5	
	101K - 400K	B, D, F, G, J	B, D, F, G, J A, B, D, F, G ±15; ±25; ±50; ±100		±5	
F Commercial	49.9 - 99.9	F, G, J	F, G	±50; ±100; ±300	±20	
	100 - 199	F, G, J	D, F, G	±25; ±50; ±100; ±300	±10	100
	200 - 999	B, D, F, G, J	B, D, F, G	±25; ±50; ±100; ±300	±5	120
	1.0K - 200K	B, D, F, G, J	A, B, D, F, G	±15; ±25; ±50; ±100; ±300	±5	

Consult factory for tighter tolerances and TCR. Custom circuits and special testing available.

General Note

IRC reserves the right to make changes in product specification without notice or liability. All information is subject to IRC's own data and is considered accurate at time of going to print.

© IRC Advanced Film Division • 4222 South Staples Street • Corpus Christi Texas 78411 USA Telephone: 361 992 7900 • Facsimile: 361 992 3377 • Website: www.irctt.com A subsidiary of TT electronics plc 4700 Series Issue January 2009 Sheet 1 of 4

TaNFilm[®] Precision SIP Network Commercial and MIL Qualified



MIL-PRF-83401 Qualification Data

Schematic	Resistance Range	Absolute Tolerance	Element Power	Size	Characteristic
С	100 - 100K	B, F, G, J	120	6, 8, 10	М, Н, К
G	100 - 100K	B, F, G, J	200	6, 8, 10	М, Н, К

Package Specification Data

Schematic	Package Power (mW)			Voltage Rating	Temperature Range	Substrate	Lead Finish	Noise
	6-pin	8-pin	10-pin					
C, F (MIL and Commercial)	600	840	1080 √PxR not to		-65°C to +125°C	99.6%	Gold Plate (60/40 Sn/Pb	<-30dB
G (MIL)	360	480	800	exceed 100V		Alumina	`available)	
G (Commercial)	600	800	1000					

Environmental Data


Test Per MIL-PRF-83401	MIL-P	RF-83401 ∆R L	TaNFilm [®] Test Data ΔR		
Test Per MIL-PRF-83401	М	к	н	Мах	Typical
Thermal Shock And Power Conditioning	±0.7%	±0.7%	±0.5%	±0.10%	±0.02%
Low Temperature Operation	±0.5%	±0.25%	±0.1%	±0.05%	±0.02%
Short-term Overload	±0.5%	±0.25%	±0.1%	±0.1%	±0.02%
Terminal Strength	±0.25%	±0.25%	±0.1%	±0.1%	±0.02%
Resistance To Solder Heat	±0.25%	±0.25%	±0.1%	±0.1%	±0.02%
Moisture Resistance	±0.5%	±0.5%	±0.4%	±0.1%	±0.02%
Shock	±0.25%	±0.25%	±0.25%	±0.1%	±0.02%
Vibration	±0.25%	±0.25%	±0.25%	±0.1%	±0.02%
Life	±2.0%	±0.5%	±0.5%	±0.1%	±0.02%
High Temperature Exposure	±1.0%	±0.5%	±0.2%	±0.1%	±0.02%
Low Temperature Storage	±0.5%	±0.25%	±0.1%	±0.1%	±0.02%
25°C Double Load	±2.0%	±0.5%	±0.5%	±0.05%	±0.02%

© IRC Advanced Film Division • 4222 South Staples Street • Corpus Christi Texas 78411 USA Telephone: 361 992 7900 • Facsimile: 361 992 3377 • Website: www.irctt.com


TaNFilm[®] Precision SIP Network Commercial and MIL Qualified



Schematic Data



Physical Data



© IRC Advanced Film Division • 4222 South Staples Street • Corpus Christi Texas 78411 USA Telephone: 361 992 7900 • Facsimile: 361 992 3377 • Website: www.irctt.com

TaNFilm[®] Precision SIP Network Commercial and MIL Qualified



Ordering Data - Commercial SIP 4781 03 1001 F в -4761 = 6-pin SIP, schematic C, gold terminations 4761SD = 6-pin SIP, schematic C, 60/40 Sn/Pb terminations 4768 = 6-pin SIP, schematic F, gold terminations 4768SD = 6-pin SIP, schematic F, 60/40 Sn/Pb terminations 4769 = 6-pin SIP, schematic G, gold terminations 4769SD = 6-pin SIP, schematic G, 60/40 Sn/Pb terminations 4781 = 8-pin SIP, schematic C, gold terminations 4781SD = 8-pin SIP, schematic C, 60/40 Sn/Pb terminations 4788 = 8-pin SIP, schematic F, gold terminations 4788SD = 8-pin SIP, schematic F, 60/40 Sn/Pb terminations 4789 = 8-pin SIP, schematic G, gold terminations 4789SD = 8-pin SIP, schematic G, 60/40 Sn/Pb terminations 4701 = 10-pin SIP, schematic C, gold terminations 4701SD = 10-pin SIP, schematic C, 60/40 Sn/Pb terminations 4708 = 10-pin SIP, schematic F, gold terminations 4708SD = 10-pin SIP, schematic F, 60/40 Sn/Pb terminations 4709 = 10-pin SIP, schematic G, gold terminations 4709SD = 10-pin SIP, schematic G, 60/40 Sn/Pb terminations $01 = \pm 100 ppm/^{\circ}C; 02 = \pm 50 ppm/^{\circ}C; 03 = \pm 25 ppm/^{\circ}C; 11 = \pm 15 ppm/^{\circ}C$ Resistance Standard 4-digit MIL resistance code Example: $1001 = 1000\Omega$; $50R0=50\Omega$ Absolute Tolerance $J = \pm 5\%$; $G = \pm 2\%$; $F = \pm 1.0\%$; $D = \pm 0.5\%$; $B = \pm 0.1\%$ Optional Ratio Tolerance to R, ••••••••••

 $F = \pm 1.0\%$; $D = \pm 0.5\%$; $C = \pm 0.25\%$; $B = \pm 0.1\%$; $A = \pm 0.05\%$; $Q = \pm 0.02\%$, $T = \pm 0.01\%$

Custom schematics and screening available.

Screening available for non-QPL values and tolerances. Contact factory for ordering information.

Ordering Data - Military (MIL-PRF-83401)

Sample Part No	- F - G
Model - M83401 = Military qualified resistor network	
Size 07 = RZ060 6-pin SIP 08 = RZ080 8-pin SIP 09 = RZ090 10-pin SIP 21 = RZ210 Hi-Rel 6-pin SIP 22 = RZ220 Hi-Rel 8-pin SIP 23 = RZ230 Hi-Rel 10-pin SIP	
Characteristic per MIL-PRF-83401 · · · · · · · · · · · · · · · · · · ·	
Resistance Standard 4-digit MIL resistance code Example: 1001 = 1000Ω; 50R0=50Ω	
Absolute Tolerance Code $J = \pm 5\%; G = \pm 2\%; F = \pm 1\%; B = \pm 0.1\%$	
Schematic · · · · · · · · · · · · · · · · · · ·	•••••

Standard termination is gold plate. Contact factory for optional 60/40 Sn/Pb hot solder dip finish. Screening available for non-QPL values and tolerances. Contact factory for ordering information.

© IRC Advanced Film Division • 4222 South Staples Street • Corpus Christi Texas 78411 USA Telephone: 361 992 7900 • Facsimile: 361 992 3377 • Website: www.irctt.com