


PROCESS DETAILS

Process	EPITAXIAL BASE
Die Size	80 x 99 MILS
Die Thickness	12.5 MILS
Base Bonding Pad Area	12 x 32 MILS
Emitter Bonding Pad Area	13 x 48 MILS
Top Side Metalization	Al - 30,000Å
Back Side Metalization	Cr/Ni/Ag 16,000Å

GEOMETRY



BACKSIDE COLLECTOR R0

GROSS DIE PER 4 INCH WAFER







1,450

PRINCIPAL DEVICE TYPES

2N3054A
CJD41C
TIP41C

145 Adams Avenue
Hauppauge, NY 11788 USA
Tel: (631) 435-1110
Fax: (631) 435-1824
www.centrasemi.com

R3 (21-September 2003)



145 Adams Avenue
Hauppauge, NY 11788 USA
Tel: (631) 435-1110
Fax: (631) 435-1824
www.centrasemi.com

R3 (21-September 2003)