

PIC-M0315H NdFeB Standard Magnet


Data

Material	NdFeB, Ni-coated	
Orientation	axially	
Remanence Br	mT	1105
Coercivity HcB	kA/m	836
Coercivity HcJ	kA/m	1274
Energy Product (BH) max.	kJ/m ³	235
Magnetic Moment M	x10 ⁻⁵ Vs cm	1.21
Operating Temperature max.	°C	120
Curie Temperature Tc	°C	340
Temperature Coefficient Tk (Br)	%/°C	-0.11
Density	g/cm ³	7.5

Nominal values unless otherwise specified

Dimensions

in mm



Customized types available.