

PIC-M0404 Bonded Permanent Magnet


Data

Material	NdFeB, bonded	
Orientation	axially	
Remanence Br	mT	575
Coercivity HcB	kA/m	378
Coercivity HcJ	kA/m	1035
Energy Product (BH) max.	kJ/m ³	64
Magnetic Moment M	x10 ⁻⁵ Vs cm	0.27
Operating Temperature max.	°C	150
Temperature Coefficient Tk(Br)	%/°C	-0.09
Density	g/cm ³	5.9

Nominal values unless otherwise specified

Dimensions

in mm



Customized types available.