

PIC-MSM-225 Threaded Magnet M5


Data

Housing Material	brass, Ni-coated	
Orientation	axially	
Remanence Br	mT	1105
Coercivity HcB	kA/m	836
Coercivity HcJ	kA/m	1274
Energy Product (BH) max.	kJ/m ³	235
Magnetic Moment M	x10 ⁻⁵ Vs cm	1.21
Operating Temperature max.	°C	120
Temperature Coefficient Tk(Br)	%/°C	-0.11

Nominal values unless otherwise specified

Dimensions

in mm



Customized types, other magnet materials and high temperature grades available.