

PIC-MSM-320

Snap-fit Miniature Magnet


Data

Housing Material	PA66, black	
Orientation	over housing length	
Remanence Br	mT	1190
Coercivity HcB	kA/m	828
Coercivity HcJ	kA/m	1512
Energy Product (BH) max.	kJ/m^3	275
Magnetic Moment M	$\times 10^{-5} \text{ Vs cm}$	2.40
Operating Temperature max.	$^{\circ}\text{C}$	85
Temperature Coefficient Tk(Br)	$\%/^{\circ}\text{C}$	-0.10

Nominal values unless otherwise specified

Dimensions

in mm



Customized types, other magnet materials and high temperature grades available.