#### **Product Facts**

- Dual wall construction
- 600, 1000 and 2500 voltage rating
- Small size, light weight
- Low smoke and low corrosive gas generation
- Resistant to most chemicals and electrical arc tracking











#### **Applications**

SPEC 44

SPEC 44 wire has a dual wall construction which combines the outstanding physical and electrical characteristics of radiation crosslinked polyalkene with the excellent mechanical and chemical properties of radiation cross-linked polyvinylidene fluoride (PVDF).

The result is a wire insulation system that offers a 150°C [302°F] temperature rating, small size, light weight, solder iron resistance, and resistance to most solvents, fuels and lubricants.

SPEC 44 wire and cable is highly flame retardant, nonmelting, does not cold flow,


Primary Insulation -

Radiation Crosslinked. Extruded Polyalkene

and though mechanically very tough, is easy to handle and install using conventional tools.

Originally developed for aerospace and military requirements in applications of high density and complex circuitry, SPEC 44 wire and cable now finds wide use throughout industry, in commercial and military electronics, avionics, on satellites, aircraft, helicopters, ships, trains, and offshore platforms where environmental conditions demand consistently reliable performance. In airframe applications SPEC 44 constructions can offer a modern dimensional

replacement for PVC/Nylon/ Glass braid type wire and cables. SPEC 44 wire is offered in a wide range of sizes in stranded conductors, standard materials available being tin or silver-plated copper and high strength copper alloy. Voltage ratings of 600, 1000 and 2500 volts are available as standard. Shielded and jacketed versions include single and multi-conductor constructions and flat braid shields where further size and weight savings are achieved.



| Available in: | Americas | Europe | Asia Pacific |  |
|---------------|----------|--------|--------------|--|
|               |          | •      |              |  |

Radiation Crosslinked.

Modified PVDF

Catalog 1654025 Revised 12-04

Dimensions are in millimeters and inches unless otherwise specified. Values in brackets are U.S. equivalents.

Dimensions are shown for reference purposes only. Specifications subject to change.

USA: 1-800-522-6752 Canada: 1-905-470-4425 Mexico: 01-800-733-8926 C. America: 52-55-5-729-0425

South America: 55-11-3611-1514 Japan: 81-44-900-5102 Singapore: 65-4866-151 UK: 44-1793-528171

SPEC 44 (Continued)

#### **Physical Characteristics**

#### **Small Size**

SPEC 44 equipment wire, 600 volt rated has a 0.19 [.008] nominal wall thickness compared to 0.25 [.010] and 0.38 [.015] for equivalent PTFE and PVC wires in MIL-W-16878, MIL-W-22759 or BS G210.

#### Light Weight

Because of the thin wall and low density of the insulation materials considerable weight savings are made over similarly rated PTFE wires, eg:- 44A0111-22AWG equipment wire 4.62 grams/meter max 22 AWG PTFE equipment wire, MIL-W-81044 5.54 grams/meter max

#### **General Handling**

The flexibility of SPEC 44 and the ease with which it takes a 'set' makes it one of the easiest of the 'high performance' wires to install. Stripping is done with conventional die blade strippers.

For details of appropriate tools see separate wire handling guide. The tin-plated conductor usually specified is easily soldered or crimped. The insulation may be hot stamp marked or printed and does not need etching before potting.

#### Lengths

SPEC 44 is available in long continuous lengths and can be supplied for use on automatic cut and strip wire preparation machines.

#### Specifications/Approvals

| MIL-W-81044, NEMA-WC-27500 (Cables)                                  |
|--|
| Def Stan. 61-12 Part 18 Issue 4 - Type 1 pliable (Maintenance Range) |
| Def Stan. 61-12 Part 26 Issue 3 Type 2, 3, 8 & 9 & METS              |
| VG 95218 Parts 20, 21, 22, 23 and 1000                               |
| NATO Stock Numbers (NSN's) exist for most standard constructions     |
| Civil Aviation Authority Accessory Approval E11623                   |
| Lloyds Register of Shipping  |
| NASA Preferred Product List  |
| Raychem Specification 44   |

#### **Typical Properties**

| Temperature rating                            | -65°C to +150°C [-85°F to +302°F] |
|---|-----------------------------------|
|   |                                   |
| Voltage rating (thin wall)                    | 600 V                             |
| Voltage rating (thick wall)                   | 2500 V                            |
| Tensile strength and elongation of insulation | 28 N/mm2 , 230%, 4000 PSI         |
| Notch propagation, 0.05mm notch               | Pass                              |
| Solder iron resistance (370°C, 1 minute)      | Pass                              |
| Shrinkage, 200°C                              | <1%                               |
| Low temperature bend                          | -65°C [-85°F]                     |
| Voltage withstand (thin wall)                 | 2500 V                            |
| Resistance: fuels, oils, solvents             | Pass                              |
|   |                                   |

www.tycoelectronics.com

SPEC 44 (Continued)

#### **Environmental Performance**

#### **Temperature Rating**

SPEC 44 wire and cable is rated for continuous operation from -65°C to +150°C  $[-85^{\circ}F \text{ to } +302^{\circ}F]$  and for short periods at temperatures as high as 300°C [572°F]. Heat ageing tests are routinely performed at temperatures of 200°C [392°F] (168 h) and 300°C [572°F] (6 h). In addition SPEC 44 insulation will not shrink back under repeated cycling.

#### Mechanical Performance

SPEC 44 wire provides better cut through resistance than some wires with much thicker walls. 600 volt equipment wire 44A0111 (0.19 mm wall) has 40% greater cut through resistance than 600 volt PTFE insulated wire (0.25 mm wall).

#### Solder Iron/Overload Resistance

The radiation crosslinking of the materials used in SPEC 44 makes them nonmelting at high temperature. As a result SPEC 44 wire is resistant to prolonged contact with solder irons and is resistant to current overloads which would melt most thermoplastic insulations.

#### **Chemical Resistance**

The irradiated dual wall construction of SPEC 44 wire is highly resistant to many acids, alkalis, hydrocarbon solvents, fuels, lubricants, water, and many missile fuels and oxidizers.

#### Cold Flow

Radiation cross-linking of SPEC 44 prevents cold flow of the insulation — a recognized problem of some uncrosslinked materials.

#### **Voltage Ratings**

Standard available voltage ratings for SPEC 44 wire are 600 volts (0.19 mm wall thickness), 1000 volts (0.28 mm wall) and 2500 volts (0.48 mm wall).

#### **Electrical Arc Track Resistance**

SPEC 44 insulation demonstrates a total resistance to arc tracking under both wet and dry conditions at aircraft system voltages.

#### Low Outgassing

For use in space applications, special constructions of SPEC 44 wire are available with low outgassing characteristics, for use in an environment of high vacuum and high temperature.


#### Fire Hazard Performance

|                       | Federal Aviation Reg FAR-25         | Pass                  |  |
|-----------------------|-------------------------------------|-----------------------|--|
|                       | BS4066 vertical flammability        | Pass                  |  |
| Flammability          | S424 14751 (Swedish chimney)        | Pass                  |  |
|                       | NFC 32070 (2) (French chimney)      | Pass                  |  |
|                       | IEC 332 part 3 (Cable ladder)       | Pass                  |  |
|                       | Smoke Index, Def Stan 61-12 (18)    | 6 per meter of wire   |  |
| Smoke/Toxicity Index  | Toxicity Index, Def Stan 61-12 (18) | 0.8 per meter of wire |  |
| Smoke/ foxicity index | Oxygen Index, NES 714               | 30% Oxygen            |  |
|                       | Temperature Index, NES 715          | >300°C [572°F]        |  |



SPEC 44 (Continued)

#### Part Numbering System




\* Classes 4, 5 and 6 available only as "44/" constructions. 44/7xxx and 44A7xxx will be available as indicated on the applicable SCD. \*\*Shield coating same as conductor coating except: - for Conductor Type 4, 6, C and D, shield shall be tin-coated copper

| Typical ordering example | 3 conductors, brown, yellow with green stripe, blue, white jacket. If 600 volt, round braid, 20 AWG tinned conductor, 44A1131-20-1/45/6-9. |
|--------------------------|--|
| Ordering information     | Other constructions and custom designed wire and cable are available on request.   |

www.tycoelectronics.com

SPEC 44 (Continued)

NEMA WC-27500 Cable Part Numbering System



Military Part No.



# **High Performance Wire and Cable**

# Raychem

**Electronics** 

Primary Wires/Twisted Pair

SPEC 44 (Continued)

44A011X (600 V) Primary Wire 44A021X (1000 V) Primary Wire

|               |          |        |       | 44A011X (600 V) |                        | 44A021X (1000 V) |                        |
|---------------|----------|--------|-------|-----------------|------------------------|------------------|------------------------|
| Wire          | Strano   | ding   | CSA   | Nom.            | Max.                   | Nom.             | Max.                   |
| Size<br>(AWG) | (mm)     | #/AWG  | (mm²) | OD              | Weight<br>(g/m) lb/kft | OD               | Weight<br>(g/m) lb/kft |
| 30            | 7/0.10   | 7/38   | 0.06  | 0.68 [0.027]    | 1.06 [0.71]            | _                | _                      |
| 28            | 7/0.13   | 7/36   | 0.09  | 0.76 [0.030]    | 1.43 [0.96]            | _                | _                      |
| 26*           | 19/0.10  | 19/38  | 0.15  | 0.86 [0.034]    | 2.08 [1.4]             | 1.02 [0.040]     | 2.38 [1.6]             |
| 24            | 19/0.13  | 19/36  | 0.25  | 1.02 [0.040]    | 2.98 [2.0]             | 1.17 [0.046]     | 3.57 [2.4]             |
| 22            | 19/0.16  | 19/34  | 0.40  | 1.19 [0.047]    | 4.46 [3.0]             | 1.37 [0.054]     | 5.20 [3.5]             |
| 20            | 19/0.20  | 19/32  | 0.60  | 1.40 [0.055]    | 6.70 [4.5]             | 1.57 [0.062]     | 7.59 [5.1]             |
| 18            | 19/0.25  | 19/30  | 1.00  | 1.65 [0.065]    | 10.12 [6.8]            | 1.85 [0.073]     | 11.46 [7.7]            |
| 16            | 19/0.29  | 19/29  | 1.25  | 1.83 [0.072]    | 12.80 [8.6]            | 2.06 [0.081]     | 14.58 [9.8]            |
| 14            | 19/0.36  | 19/27  | 2.00  | 2.26 [0.089]    | 19.64 [13.2]           | 2.49 [0.098]     | 21.88 [14.7]           |
| 12            | 37/0.32  | 37/28  | 3.00  | 2.74 [0.108]    | 30.06 [20.0]           | 2.97 [0.117]     | 32.89 [22.1]           |
| 10            | 37/0.40  | 37/26  | 5.00  | 3.28 [0.129]    | 46.28 [31.1]           | 3.71 [0.146]     | 52.98 [35.6]           |
| 8             | 133/0.29 | 133/29 | _     | _               | _                      | 5.23 [0.206]     | 91.97 [61.8]           |

<sup>\*</sup>For 44A0211-26 the stranding is 7/0.16mm 7/34 AWG





44A031X (2500 V) Primary Wire 44A081X (600 V) Airframe Wire 44A012X (600 V) Twisted Pair

| 44A031X (2500 V) |                                | 44A081)       | ( (600 V)                     | 44A012X (1000 V) |                                |
|------------------|--------------------------------|---------------|-------------------------------|------------------|--------------------------------|
| Nom.<br>OD       | Max.<br>Weight<br>(g/m) lb/kft | Nom.<br>OD    | Max<br>Weight<br>(g/m) lb/kft | Nom.<br>OD       | Max.<br>Weight<br>(g/m) lb/kft |
| _                | _                              | _             | _                             | 1.37 [0.054]     | 2.38 [1.6]                     |
| _                | _                              | _             | _                             | 1.52 [0.060]     | 3.13 [2.1]                     |
| 1.35 [0.053]     | 3.13 [2.1]                     | 1.22 [0.048]  | 2.98 [2.0]                    | 1.73 [0.068]     | 4.47 [3.0]                     |
| 1.44 [0.057]     | 4.46 [3.0]                     | 1.37 [0.054]  | 3.87 [2.6]                    | 2.03 [0.080]     | 6.69 [4.5]                     |
| 1.75 [0.069]     | 6.40 [4.3]                     | 1.57 [0.062]  | 5.65 [3.8]                    | 2.38 [0.094]     | 9.82 [6.6]                     |
| 1.98 [0.078]     | 9.08 [6.1]                     | 1.78 [0.070]  | 8.04 [5.4]                    | 2.79 [0.110]     | 14.73 [9.9]                    |
| 2.23 [0.088]     | 12.95 [8.7]                    | 2.03 [0.080]  | 11.91 [8.0]                   | 3.30 [0.130]     | 22.32 [15.0]                   |
| 2.46 [0.097]     | 16.22 [10.9]                   | 2.26 [0.089]  | 14.73 [9.9]                   | 3.65 [0.144]     | 28.42 [19.1]                   |
| 2.92 [0.115]     | 24.10 [16.2]                   | 2.74 [0.108]  | 22.17 [14.9]                  | 4.52 [0.178]     | 44.35 [29.8]                   |
| 3.32 [0.131]     | 36.01 [24.2]                   | 3.20 [0.126]  | 32.59 [21.9]                  | 5.48 [0.216]     | 69.00 [46.5]                   |
| 4.09 [0.161]     | 54.32 [36.5]                   | 3.94 [0.155]  | 52.08 [35.0]                  | _                | _                              |
| 96.20 [0.219]    | 96.73 [65.0]                   | 92.94 [0.214] | 93.46 [62.8]                  | _                | _                              |

www.tycoelectronics.com



# High Performance Wire and Cable

# Raychem

**Electronics** 

Shielded and Jacketed Cable

SPEC 44 (Continued)





44A111X (600 V) 1 Conductor

44A121X (600 V) 1 Conductor

| Wire Size (AWG)     Stranding (Mm)     #/AWG     Nom. OD     Max. Weight (g/m) lb/kft (g/m) lb/kft     Nom. OD     Max. Weight (g/m) lb/kft       30     7/0.10     7/38     1.47 [0.058]     5.20 [3.5]     —     —       28     7/0.13     7/36     1.55 [0.061]     5.80 [3.9]     1.60 [0.063]     5.65 [3.8]       26     19/0.10     19/38     1.57 [0.065]     6.84 [4.6]     1.73 [0.068]     6.85 [4.6]       24     19/0.13     19/36     1.83 [0.072]     8.63 [5.8]     1.98 [0.078]     9.67 [6.5]       22     19/0.16     19/34     2.01 [0.079]     10.71 [7.2]     2.24 [0.088]     12.35 [8.3]       20     19/0.20     19/32     2.26 [0.089]     14.73 [9.9]     2.54 [0.100]     17.41 [11.7]       18     19/0.25     19/30     2.62 [0.103]     20.68[13.9]     2.82 [0.111]     22.62 [15.2]       16     19/0.29     19/29     2.79 [0.110]     24.55 [16.5]     3.02 [0.119]     26.64 [17.9]       14     19/0.36     19/27     3.22 [0.127]     34.08 [22.9]     3.45 [0.136] <td< th=""><th></th><th></th><th></th><th>44A11</th><th colspan="2">44A111X (600 V)</th><th>(600 V)</th></td<> |         |         |       | 44A11        | 44A111X (600 V) |              | (600 V)      |
|--|---------|---------|-------|--------------|-----------------|--------------|--------------|
| Size (AWG)     (mm)     #/AWG     OD     Weight (g/m) lb/kft     OD     Weight (g/m) lb/kft       30     7/0.10     7/38     1.47 [0.058]     5.20 [3.5]     —     —     —       28     7/0.13     7/36     1.55 [0.061]     5.80 [3.9]     1.60 [0.063]     5.65 [3.8]       26     19/0.10     19/38     1.57 [0.065]     6.84 [4.6]     1.73 [0.068]     6.85 [4.6]       24     19/0.13     19/36     1.83 [0.072]     8.63 [5.8]     1.98 [0.078]     9.67 [6.5]       22     19/0.16     19/34     2.01 [0.079]     10.71 [7.2]     2.24 [0.088]     12.35 [8.3]       20     19/0.20     19/32     2.26 [0.089]     14.73 [9.9]     2.54 [0.100]     17.41 [11.7]       18     19/0.25     19/30     2.62 [0.103]     20.68[13.9]     2.82 [0.111]     22.62 [15.2]       16     19/0.29     19/29     2.79 [0.110]     24.55 [16.5]     3.02 [0.119]     26.64 [17.9]       14     19/0.36     19/27     3.22 [0.127]     34.08 [22.9]     3.45 [0.136]     36.16 [24.3]   | WireStr |         | ling  | Nom          | Max.            | Nom          | Max.         |
| 28     7/0.13     7/36     1.55 [0.061]     5.80 [3.9]     1.60 [0.063]     5.65 [3.8]       26     19/0.10     19/38     1.57 [0.065]     6.84 [4.6]     1.73 [0.068]     6.85 [4.6]       24     19/0.13     19/36     1.83 [0.072]     8.63 [5.8]     1.98 [0.078]     9.67 [6.5]       22     19/0.16     19/34     2.01 [0.079]     10.71 [7.2]     2.24 [0.088]     12.35 [8.3]       20     19/0.20     19/32     2.26 [0.089]     14.73 [9.9]     2.54 [0.100]     17.41 [11.7]       18     19/0.25     19/30     2.62 [0.103]     20.68[13.9]     2.82 [0.111]     22.62 [15.2]       16     19/0.29     19/29     2.79 [0.110]     24.55 [16.5]     3.02 [0.119]     26.64 [17.9]       14     19/0.36     19/27     3.22 [0.127]     34.08 [22.9]     3.45 [0.136]     36.16 [24.3]  |         | (mm)    | #/AWG |              |                 |              |              |
| 26     19/0.10     19/38     1.57 [0.065]     6.84 [4.6]     1.73 [0.068]     6.85 [4.6]       24     19/0.13     19/36     1.83 [0.072]     8.63 [5.8]     1.98 [0.078]     9.67 [6.5]       22     19/0.16     19/34     2.01 [0.079]     10.71 [7.2]     2.24 [0.088]     12.35 [8.3]       20     19/0.20     19/32     2.26 [0.089]     14.73 [9.9]     2.54 [0.100]     17.41 [11.7]       18     19/0.25     19/30     2.62 [0.103]     20.68[13.9]     2.82 [0.111]     22.62 [15.2]       16     19/0.29     19/29     2.79 [0.110]     24.55 [16.5]     3.02 [0.119]     26.64 [17.9]       14     19/0.36     19/27     3.22 [0.127]     34.08 [22.9]     3.45 [0.136]     36.16 [24.3]   | 30      | 7/0.10  | 7/38  | 1.47 [0.058] | 5.20 [3.5]      | _            | _            |
| 24     19/0.13     19/36     1.83 [0.072]     8.63 [5.8]     1.98 [0.078]     9.67 [6.5]       22     19/0.16     19/34     2.01 [0.079]     10.71 [7.2]     2.24 [0.088]     12.35 [8.3]       20     19/0.20     19/32     2.26 [0.089]     14.73 [9.9]     2.54 [0.100]     17.41 [11.7]       18     19/0.25     19/30     2.62 [0.103]     20.68[13.9]     2.82 [0.111]     22.62 [15.2]       16     19/0.29     19/29     2.79 [0.110]     24.55 [16.5]     3.02 [0.119]     26.64 [17.9]       14     19/0.36     19/27     3.22 [0.127]     34.08 [22.9]     3.45 [0.136]     36.16 [24.3]  | 28      | 7/0.13  | 7/36  | 1.55 [0.061] | 5.80 [3.9]      | 1.60 [0.063] | 5.65 [3.8]   |
| 22 19/0.16 19/34 2.01 [0.079] 10.71 [7.2] 2.24 [0.088] 12.35 [8.3]   20 19/0.20 19/32 2.26 [0.089] 14.73 [9.9] 2.54 [0.100] 17.41 [11.7]   18 19/0.25 19/30 2.62 [0.103] 20.68[13.9] 2.82 [0.111] 22.62 [15.2]   16 19/0.29 19/29 2.79 [0.110] 24.55 [16.5] 3.02 [0.119] 26.64 [17.9]   14 19/0.36 19/27 3.22 [0.127] 34.08 [22.9] 3.45 [0.136] 36.16 [24.3]   | 26      | 19/0.10 | 19/38 | 1.57 [0.065] | 6.84 [4.6]      | 1.73 [0.068] | 6.85 [4.6]   |
| 20 19/0.20 19/32 2.26 [0.089] 14.73 [9.9] 2.54 [0.100] 17.41 [11.7]   18 19/0.25 19/30 2.62 [0.103] 20.68[13.9] 2.82 [0.111] 22.62 [15.2]   16 19/0.29 19/29 2.79 [0.110] 24.55 [16.5] 3.02 [0.119] 26.64 [17.9]   14 19/0.36 19/27 3.22 [0.127] 34.08 [22.9] 3.45 [0.136] 36.16 [24.3]  | 24      | 19/0.13 | 19/36 | 1.83 [0.072] | 8.63 [5.8]      | 1.98 [0.078] | 9.67 [6.5]   |
| 18 19/0.25 19/30 2.62 [0.103] 20.68[13.9] 2.82 [0.111] 22.62 [15.2]   16 19/0.29 19/29 2.79 [0.110] 24.55 [16.5] 3.02 [0.119] 26.64 [17.9]   14 19/0.36 19/27 3.22 [0.127] 34.08 [22.9] 3.45 [0.136] 36.16 [24.3]  | 22      | 19/0.16 | 19/34 | 2.01 [0.079] | 10.71 [7.2]     | 2.24 [0.088] | 12.35 [8.3]  |
| 16 19/0.29 19/29 2.79 [0.110] 24.55 [16.5] 3.02 [0.119] 26.64 [17.9]   14 19/0.36 19/27 3.22 [0.127] 34.08 [22.9] 3.45 [0.136] 36.16 [24.3]  | 20      | 19/0.20 | 19/32 | 2.26 [0.089] | 14.73 [9.9]     | 2.54 [0.100] | 17.41 [11.7] |
| 14 19/0.36 19/27 3.22 [0.127] 34.08 [22.9] 3.45 [0.136] 36.16 [24.3]   | 18      | 19/0.25 | 19/30 | 2.62 [0.103] | 20.68[13.9]     | 2.82 [0.111] | 22.62 [15.2] |
|  | 16      | 19/0.29 | 19/29 | 2.79 [0.110] | 24.55 [16.5]    | 3.02 [0.119] | 26.64 [17.9] |
| 12 37/0.32 37/28 3.70 [0.146] 47.77 [32.1] 4.14 [0.155] 49.56 [33.3]   | 14      | 19/0.36 | 19/27 | 3.22 [0.127] | 34.08 [22.9]    | 3.45 [0.136] | 36.16 [24.3] |
|  | 12      | 37/0.32 | 37/28 | 3.70 [0.146] | 47.77 [32.1]    | 4.14 [0.155] | 49.56 [33.3] |

Other sizes are also available in some constructions depending on conductor type and construction required.





44A181X (600 V) 1 Conductor

44A112X (600 V) 2 Conductor

|                       | 44A181X      | ( (600 V)                      | 44A112X (600 V) |                                |
|-----------------------|--------------|--------------------------------|-----------------|--------------------------------|
| Wire<br>Size<br>(AWG) | Nom.<br>OD   | Max.<br>Weight<br>(g/m) lb/kft | Nom.<br>OD      | Max.<br>Weight<br>(g/m) lb/kft |
| 30                    | _            | _                              | 2.23 [0.088]    | 8.63 [5.8]                     |
| 28                    | _            | _                              | 2.38 [0.094]    | 9.82 [6.6]                     |
| 26                    | _            | _                              | 2.59 [0.102]    | 12.05 [8.1]                    |
| 24                    | 2.26 [0.089] | 11.76 [ 7.9]                   | 2.99 [0.118]    | 16.82 [11.3]                   |
| 22                    | 2.57 [0.101] | 15.48 [10.4]                   | 3.35 [0.132]    | 21.57 [14.5]                   |
| 20                    | 2.77 [0.109] | 19.19 [12.9]                   | 3.76 [0.148]    | 27.97 [18.8]                   |
| 18                    | 3.02 [0.119] | 24.11 [16.2]                   | 4.32 [0.170]    | 38.24 [25.7]                   |
| 16                    | 3.25 [0.128] | 28.13 [18.9]                   | 4.67 [0.184]    | 44.94 [30.2]                   |
| 14                    | 3.73 [0.147] | 38.69 [26.0]                   | 5.53 [0.218]    | 64.28 [43.2]                   |
| 12                    | 4.19 [0.165] | 52.38 [35.2]                   | 6.50 [0.256]    | 91.51 [61.5]                   |

Other sizes are also available in some constructions depending on conductor type and construction required.