

## SPECIFICATION CONTROL DRAWING

55/0114


WIRE, RADIATION-CROSSLINKED, MODIFIED ETFE INSULATED,

LIGHTWEIGHT, OUTER SPACE, 600 VOLT

2-28-05

Revision \_

This specification sheet forms a part of the latest issue of Raychem Specification 55/.



LOWOUTGASSING, RADIATION-CROSSLINKED, MODIFIEDETFE

TABLE I. CONSTRUCTION DETAILS									
			DIAMETER OF		FINISHEDWIRE				
PARTNUMBER 1/	WIRE SIZE (AWG)	CONDUCTOR STRANDING (number x AWG)	STR/ CONE	ANDED DUCTOR in.)	MAXIMUM RESISTANCE AT 20°C	DIAMETER (in.)	MAXIMUM WEIGHT (lb/1000 ft)		
			MINIMUM	MAXIMUM	(ohms /1000 ft.)		(,		
55/0114-30-*	30	7 x 38	.011	.012	117.4	.024 ± .002	.66		
55/0114-28-*	28	7 x 36	.014	.016	74.4	.027 ± .002	.91		
55/0114-26-*	26	19 x 38	.018	.020	44.8	.032 ± .002	1.4		
55/0114-24-*	24	19 x 36	.023	.025	28.4	.037 ± .002	2.0		
55/0114-22-*	22	19 x 34	.029	.031	17.5	.043 ± .002	2.9		
55/0114-20-*	20	19 x 32	.037	.039	10.7	.050 ± .002	4.4		
55/0114-18-*	18	19 x 30	.046	.050	6.8	.060 ± .002	6.5		
55/0114-16-*	16	19 x 29	.052	.057	5.3	.068 ± .002	8.3		

TABLE II. PERFORMANCE DETAILS					
PARTNUMBER	BENDTESTING				
	MANDRELDIAMETER (inch) (± 3%)	WEIGHT (lb) (± 3%)			
<u>1</u> /	CROSSLINKVERIFICATION	CROSSLINKVERIFICATION			
55/0114-30-*	.250	.125			
55/0114-28-*	.250	.125			
55/0114-26-*	.375	.125			
55/0114-24-*	.375	.250			
55/0114-22-*	.500	.375			
55/0114-20-*	.500	.500			
55/0114-18-*	.500	.500			
55/0114-16-*	.750	.750			

## WIRE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 200°C

Maximum continuous conductor temperature VOLTAGE RATING: 600 volts (rms) at sea level CROSSLINK VERIFICATION: 300 ± 3°C for 1 hour

COLOR: White preferred

IDENTIFICATION AND COLOR STRIPING DURABILITY: 125 cycles (250 strokes) (minimum), 500 g weight

INSULATION ELONGATION: 50% (minimum)

**INSULATION FLAWS:** 

Spark Test, 3.0 kV (rms)

Impulse Dielectric Test, 8.0 kV (peak) INSULATION THICKNESS: .005 in. (minimum)

RADIATION RESISTANCE: 500 megarads

SHRINKAGE:  $230 \pm 3^{\circ}$ C for 1 hour, 0.125 in. (maximum) in 12 in.

VACUUM STABILITY:

Total Mass Loss (TML), 1.0% (maximum) Volitale Condensable Material, 0.1% (maximum) VOLTAGE WITHSTAND TEST (Post Environmental): 2500 volts (rms), 60 Hz, 5 minutes

## PARTNUMBER:

The "\*" in the part numbers above shall be replaced by color code designators.

1/ Example: AWG 20, white: 55/0114-20-9

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice.

Tyco Electronics also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.

1/COLORS AND COLOR CODE DESIGNATORS SHALL BE IN ACCORDANCE WITH MIL-STD-681. OTHER CODES AND SUFFIXES MAY BE ADDED TO THE PART NUMBER, AS NECESSARY, TO CAPTURE ANY ADDITIONAL REQUIREMENTS IMPOSED BY THE PURCHASE ORDER.

\_\_\_\_\_\_

DIMENSIONS ARE IN INCHES, AND UNLESS OTHERWISE DESIGNATED ARE NOMINAL

THIS SPECIFICATION SHEET TAKES PRECEDENCE OVER DOCUMENTS REFERENCED HEREIN. REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATION FOR BID



Raychem Wire & Cable 501 Oakside Avenue Redwood City, CA 94063-3800 Phone: 1-800-227-8816 Fax: 1-650-361-6297

Page 1 of 1